# MACOMASS TPE MM-TPE-V 5050

### Thermoplastic Elastomer

MACOMASS Verkaufs AG

#### Message:

MACOMASS TPE MM-TPE-V 5050 is a thermoplastic elastomer (TPE) material. This product is available in Europe and is processed by extrusion. The main features of the MACOMASS TPE MM-TPE-V 5050 are: Good UV resistance chemical resistance UV stability

| General Information                  |                          |       |             |
|--------------------------------------|--------------------------|-------|-------------|
| Additive                             | UV stabilizer            |       |             |
| Features                             | Good UV resistance       |       |             |
|                                      | Good chemical resistance |       |             |
|                                      |                          |       |             |
| Appearance                           | Black                    |       |             |
| Forms                                | Particle                 |       |             |
| Processing Method                    | Extrusion                |       |             |
| Physical                             | Nominal Value            | Unit  | Test Method |
| Density                              | 0.940 - 0.980            | g/cm³ | ISO 1183    |
| Hardness                             | Nominal Value            | Unit  | Test Method |
| Durometer Hardness (Shore A, 15 sec) | 82 - 88                  |       | ISO 868     |
| Elastomers                           | Nominal Value            | Unit  | Test Method |
| Tensile Stress (Yield)               | > 10.0                   | MPa   | ISO 37      |
| Tensile Elongation (Break)           | > 350                    | %     | ISO 37      |
| Tear Strength                        | > 25                     | kN/m  | ISO 34-1    |
| Compression Set                      | < 50                     | %     | ISO 815     |
| Extrusion                            | Nominal Value            | Unit  |             |
| Drying Temperature                   | 80.0                     | °C    |             |
| Drying Time                          | 2.0                      | hr    |             |
| Melt Temperature                     | 160 - 230                | °C    |             |
| Extrusion instructions               |                          |       |             |
|                                      |                          |       |             |

Compression ratio: 1:2.5 to 1:3

The information and data on this page are provided by manufacturers and document providers. SHANGHAI SUSHENG assumes no legal liability. It is strongly recommended to verify all technical data with material suppliers before final material selection. All rights belong to the original authors. If any infringement occurs, please contact us immediately.

#### Recommended distributors for this material

## Susheng Import & Export Trading Co.,Ltd.

Tel: +86 21 5895 8519 Phone: +86 13424755533 Email: sales@su-jiao.com

No. 215, Lianhe North Road, Fengxian District, Shanghai, China

