

Baydur® 641 IBS (25 pcf)

Polyurethane (MDI)

Covestro - PUR

Message:

Baydur 641 IBS is a rigid polyurethane structural foam system used in the reaction injection molding (RIM) process. This system is supplied as two reactive liquid components and is typically used with a blowing paste purchased separately. Component A is a polymeric diphenylmethane diisocyanate (PMDI). Component B is a formulated polyol system containing no CFC- or HCFC-blowing additives. The blowing paste is Baydur PU-1731. The Baydur 641 IBS system is used in the industrial and medical equipment markets for applications requiring dimensional stability and excellent surface finish, such as, rollers for photographic and X-ray film processing equipment. As with any product, use of Baydur 641 IBS system in a given application must be tested (including field testing, etc.) in advance by the user to determine suitability.

General Information			
Features	Good dimensional stability		
	Excellent appearance		
Uses	Structural Foam		
	Industrial application		
	Medical/nursing supplies		
Processing Method	Reaction Injection Molding (RIM)		
Physical	Nominal Value	Unit	Test Method
Specific Gravity	0.399	g/cm³	ASTM D792
Molding Shrinkage - Flow (12.7 mm)	0.30 - 0.50	%	ASTM D955
Hardness	Nominal Value	Unit	Test Method
Durometer Hardness (Shore D, 12.7 mm)	50		ASTM D2240
Mechanical	Nominal Value	Unit	Test Method
Tensile Strength (Break, 12.7 mm)	7.58	MPa	ASTM D638
Tensile Elongation (Break, 12.7 mm)	8.0	%	ASTM D638
Flexural Modulus (12.7 mm)	372	MPa	ASTM D790
Flexural Strength (12.7 mm)	14.5	MPa	ASTM D790
Compressive Strength (12.7 mm)	6.21	MPa	ASTM D695
Impact	Nominal Value	Unit	Test Method
Charpy Unnotched Impact Strength ¹	7.1	kJ/m²	Internal method
Thermal	Nominal Value	Unit	Test Method
Deflection Temperature Under Load (0.45 MPa, unannealed, 12.7mm)	65.0	°C	ASTM D648
Thermoset	Nominal Value		
Thermoset Components			
Component a	Mixing ratio by weight: 110		
Component B	Mixing ratio by weight: 100		
Additional Information			

Part A

Type: Isocyanate

Appearance: Dark brown liquid

Specific Gravity @ 25°C: 1.24

Viscosity @25°C: 200 cps

Flash Point PMCC: 199°C

NCO: 31.5 wt%

Part B

Type: Polyol

Appearance: Pale yellow liquid

Specific Gravity @ 25°C: 1.02

Viscosity @25°C: 2000 cps

Flash Point PMCC: 187°C

Water: 0.45 wt%

Hydroxyl Number: 367 KOH/g

Material Temperatures: 27 to 35°C Mold Temperature: 60 to 70°C Hand Mix Reactivity at 25°C

Cream Time: 8 to 13 sec

Gel Time: 15 to 25 sec

Tack Free Time: 23 to 28 sec

Free-Rise Density: 7.5 to 10 lb/ft³

Polyol Nucleation Specific Gravity: 0.85 to 0.90 Typical cure Time, 0.500 in Thickness: 4 sec

NOTE

1. 0.5 in

The information and data on this page are provided by manufacturers and document providers. SHANGHAI SUSHENG assumes no legal liability. It is strongly recommended to verify all technical data with material suppliers before final material selection. All rights belong to the original authors. If any infringement occurs, please contact us immediately.

Recommended distributors for this material

Susheng Import & Export Trading Co.,Ltd.

Tel: +86 21 5895 8519

Phone: +86 13424755533

Email: sales@su-jiao.com

No. 215, Lianhe North Road, Fengxian District, Shanghai, China



WECHAT