

VESTAKEEP® 2000UFP20

Polyetheretherketone

Evonik Industries AG

Message:

Medium-viscosity, unreinforced polyether ether ketone

VESTAKEEP 2000UFP20 is an unreinforced, medium-viscosity polyether ether ketone ultra-fine powder. The product can be used for coatings according to the tribo-method or it can be applied in a suspension.

The semi-crystalline polymer features superior thermal and chemical resistance. Parts made from VESTAKEEP 2000UFP20 are self-extinguishing.

General Information			
Features	Good Chemical Resistance Medium Viscosity Self Extinguishing Semi Crystalline		
Forms	Powder		
Physical	Nominal Value	Unit	Test Method
Density	1.30	g/cm ³	ISO 1183
Apparent Density	0.27	g/cm ³	ISO 60
Melt Volume-Flow Rate (MVR) (380°C/5.0 kg)	70.0	cm ³ /10min	ISO 1133
Average Particle Size - d50 ¹	20	µm	
Mechanical	Nominal Value	Unit	Test Method
Tensile Modulus	3700	MPa	ISO 527-2
Tensile Stress (Yield)	100	MPa	ISO 527-2
Tensile Strain			ISO 527-2
Yield	5.0	%	
Break	30	%	
Impact	Nominal Value	Unit	Test Method
Charpy Notched Impact Strength			ISO 179/1eA
-30°C, Complete Break	6.0	kJ/m ²	
23°C, Complete Break	6.0	kJ/m ²	
Charpy Unnotched Impact Strength			ISO 179/1eU
-30°C	No Break		
23°C	No Break		
Thermal	Nominal Value	Unit	Test Method
Heat Deflection Temperature			
0.45 MPa, Unannealed	205	°C	ISO 75-2/B
1.8 MPa, Unannealed	155	°C	ISO 75-2/A
Vicat Softening Temperature			
--	335	°C	ISO 306/A

--	310	°C	ISO 306/B
Melting Temperature ²	340	°C	ISO 11357-3
Flammability	Nominal Value		Test Method
Flame Rating (3.20 mm)	V-0		UL 94
NOTE			
1.	Malvern Mastersizer		
2.	2nd heating		

The information and data on this page are provided by manufacturers and document providers. SHANGHAI SUSHENG assumes no legal liability. It is strongly recommended to verify all technical data with material suppliers before final material selection. All rights belong to the original authors. If any infringement occurs, please contact us immediately.

Recommended distributors for this material

Susheng Import & Export Trading Co.,Ltd.

Tel: +86 21 5895 8519

Phone: +86 13424755533

Email: sales@su-jiao.com

No. 215, Lianhe North Road, Fengxian District, Shanghai, China

