

SCANTEC PC S75R V0

Polycarbonate

Polykemi AB

Message:

Flame retardant

General Information			
Additive	Flame Retardant		
Features	Flame Retardant		
Physical	Nominal Value	Unit	Test Method
Density	1.24	g/cm ³	ISO 1183
Molding Shrinkage			ISO 294-4
Across Flow	0.50 to 0.70	%	
Flow	0.50 to 0.70	%	
Mechanical	Nominal Value	Unit	Test Method
Tensile Stress	60.0	MPa	ISO 527-2
Tensile Strain (Yield)	6.0	%	ISO 527-2
Flexural Modulus (23°C)	2400	MPa	ISO 178
Flexural Stress	105	MPa	ISO 178
Impact	Nominal Value	Unit	Test Method
Charpy Notched Impact Strength (23°C)	25	kJ/m ²	ISO 179
Thermal	Nominal Value	Unit	Test Method
Heat Deflection Temperature ¹			
0.45 MPa, Unannealed	135	°C	ISO 75-2/B
1.8 MPa, Unannealed	125	°C	ISO 75-2/A
Vicat Softening Temperature	140	°C	ISO 306/B50
Flammability	Nominal Value	Unit	Test Method
Flame Rating (1.60 mm)	V-0		UL 94
Glow Wire Ignition Temperature (2.00 mm)	960	°C	IEC 60695-2-13
NOTE			

1. 120°C/hr

The information and data on this page are provided by manufacturers and document providers. SHANGHAI SUSHENG assumes no legal liability. It is strongly recommended to verify all technical data with material suppliers before final material selection. All rights belong to the original authors. If any infringement occurs, please contact us immediately.

Recommended distributors for this material

Susheng Import & Export Trading Co.,Ltd.

Tel: +86 21 5895 8519
Phone: +86 13424755533
Email: sales@su-jiao.com

No. 215, Lianhe North Road, Fengxian District, Shanghai, China

