

LITEN ML 67

Polyethylene Copolymer
UNIPETROL RPA

Message:

LITEN ML 67 is a linear polyethylene, copolymer with narrow molecular weight distribution and higher resistance to UV radiation, intended for injection moulding. It is suitable for manufacture of large containers, pallets, technical parts and other products for outdoor use, requiring very good impact strength.

LITEN ML 67 meets the hygienic requirements on materials and articles intended for contact with foodstuffs according to Regulation (EC) 1935/2004 of the European Parliament and of the Council, as well as according to Commission Regulation (EU) No 10/2011 including changes and additions.

General Information			
Features	Copolymer		
	Food Contact Acceptable		
	Good Impact Resistance		
	Good UV Resistance		
	Narrow Molecular Weight Distribution		
Uses	Containers		
	Engineering Parts		
	Outdoor Applications		
Agency Ratings	EC 1935/2004		
	EU 10/2011		
Forms	Pellets		
Processing Method	Injection Molding		
Physical	Nominal Value	Unit	Test Method
Density	0.954	g/cm ³	ISO 1183
Melt Mass-Flow Rate (MFR)			ISO 1133
190°C/2.16 kg	6.5	g/10 min	
190°C/5.0 kg	18	g/10 min	
Hardness	Nominal Value	Unit	Test Method
Shore Hardness (Shore D)	57		ISO 868
Mechanical	Nominal Value	Unit	Test Method
Tensile Stress (Yield)	22.0	MPa	ISO 527-2
Tensile Strain (Yield)	10	%	ISO 527-2
Flexural Modulus	900	MPa	ISO 178
Impact	Nominal Value	Unit	Test Method
Charpy Notched Impact Strength			ISO 179
-30°C	5.5	kJ/m ²	
23°C	7.0	kJ/m ²	

Thermal	Nominal Value	Unit	Test Method
Vicat Softening Temperature	125	°C	ISO 306

The information and data on this page are provided by manufacturers and document providers. SHANGHAI SUSHENG assumes no legal liability. It is strongly recommended to verify all technical data with material suppliers before final material selection. All rights belong to the original authors. If any infringement occurs, please contact us immediately.

Recommended distributors for this material

Susheng Import & Export Trading Co.,Ltd.

Tel: +86 21 5895 8519
Phone: +86 13424755533
Email: sales@su-jiao.com
No. 215, Lianhe North Road, Fengxian District, Shanghai, China

