

# Cereplast Compostables® 3020

Polylactic Acid  
Trellis Bioplastics

Message:

Cereplast Compostables® resins are renewable, ecologically sound substitutes for petroleum-based plastic product, replacing nearly 100% of the petroleum-based additives used in traditional plastics. Cereplast Compostables® resins are using polymer and additives derived from starch and other renewable resources chemistry. These components are carefully blended together on state-of-the-art compounding equipments.

All Cereplast Compostables® resins, including Compostable 3020, are certified as biodegradable and compostable in the United States and Europe, meeting BPI (Biodegradable Products Institute [www.bpiworld.com](http://www.bpiworld.com)) standards for compostability (ASTM6400D99, ASTM6868) and European Bioplastics Standards (EN13432).

Compostable 3020 has been designed to have an excellent balance of puncture strength, toughness and processability. Compostable 3020 can be processed on existing blown film extrusion machines. Please see our processing guide for processing and material drying guidelines. This can be found at [www.cereplast.com](http://www.cereplast.com).

Compostable 3020 is recommended for extrusion of blown film for application like liners, bags, packaging, overwrap, and more...

General Information			
Features	Environmental protection		
	Perforation resistance		
	Comstable		
	Updatable resources		
	Workability, good		
	Good toughness		
	Biodegradable		
Uses	Blown Film		
	Packaging		
	Lining		
	Bags		
Agency Ratings	ASTM D 6400		
	ASTM D 6868		
	EN 13432		
Processing Method	Film extrusion		
	Blow film		
Physical	Nominal Value	Unit	Test Method
Specific Gravity	1.36	g/cm³	ASTM D792A
Melt Mass-Flow Rate (MFR) (190°C/2.16 kg)	4.1	g/10 min	ASTM D1238
Mechanical	Nominal Value	Unit	Test Method
Tensile Modulus	400	MPa	ASTM D638
Tensile Strength (Break)	18.4	MPa	ASTM D638

Flexural Modulus	328	MPa	ASTM D790
Flexural Strength	12.0	MPa	ASTM D790
Impact	Nominal Value	Unit	Test Method
Dart Drop Impact	> 18.0	J	ASTM D5420

The information and data on this page are provided by manufacturers and document providers. SHANGHAI SUSHENG assumes no legal liability. It is strongly recommended to verify all technical data with material suppliers before final material selection. All rights belong to the original authors. If any infringement occurs, please contact us immediately.

#### Recommended distributors for this material

### Susheng Import & Export Trading Co.,Ltd.

Tel: +86 21 5895 8519

Phone: +86 13424755533

Email: sales@su-jiao.com

No. 215, Lianhe North Road, Fengxian District, Shanghai, China

