

ColorRx® POM2-0800RX

Acetal (POM) Copolymer

LTL Color Compounders, Inc.

Message:

A biocompatible, standard flow grade POM Copolymer for healthcare applications.

General Information			
Features	Biocompatible Copolymer		
Uses	Medical/Healthcare Applications		
Agency Ratings	ISO 10993 USP Class VI		
Physical	Nominal Value	Unit	Test Method
Specific Gravity	1.41	g/cm ³	ASTM D792
Melt Volume-Flow Rate (MVR) (190°C/2.16 kg)	8.00	cm ³ /10min	ASTM D1238
Molding Shrinkage - Flow	2.0	%	ASTM D955
Water Absorption (Saturation, 23°C)	0.65	%	ASTM D570
Mechanical	Nominal Value	Unit	Test Method
Tensile Strength (Yield)	63.3	MPa	ASTM D638
Tensile Elongation			ASTM D638
Yield	9.0	%	
Break	30	%	
Flexural Modulus	2700	MPa	ASTM D790
Thermal	Nominal Value	Unit	Test Method
Deflection Temperature Under Load (1.8 MPa, Unannealed, 3.20 mm)	104	°C	ASTM D648

The information and data on this page are provided by manufacturers and document providers. SHANGHAI SUSHENG assumes no legal liability. It is strongly recommended to verify all technical data with material suppliers before final material selection. All rights belong to the original authors. If any infringement occurs, please contact us immediately.

Recommended distributors for this material

Susheng Import & Export Trading Co.,Ltd.

Tel: +86 21 5895 8519

Phone: +86 13424755533

Email: sales@su-jiao.com

No. 215, Lianhe North Road, Fengxian District, Shanghai, China



WECHAT