

Hostacom 65F4-4C

Polypropylene Homopolymer
LyondellBasell Industries

Message:

Hostacom 65F4-4C conventional melt flow, 2,900 MPa flexural modulus, precolored, 40% talc-filled polypropylene homopolymer is designed for maximum stiffness, good dimensional stability and excellent heat aging performance.

General Information			
UL YellowCard	E229217-102026871		
Filler / Reinforcement	Talc,40% Filler by Weight		
Features	Good Dimensional Stability		
	Good Heat Aging Resistance		
	Good Stiffness		
Uses	Appliances		
	Automotive Applications		
	Household Goods		
Appearance	Unspecified Color		
Forms	Pellets		
Processing Method	Injection Molding		
Physical	Nominal Value	Unit	Test Method
Specific Gravity	1.25	g/cm ³	ASTM D792
Melt Mass-Flow Rate (MFR) (230°C/2.16 kg)	4.0	g/10 min	ASTM D1238
Hardness	Nominal Value	Unit	Test Method
Rockwell Hardness (R-Scale)	94		ASTM D785
Mechanical	Nominal Value	Unit	Test Method
Tensile Strength			ASTM D638
Yield	29.0	MPa	
Break	23.0	MPa	
Tensile Elongation			ASTM D638
Yield	4.0	%	
Break	20	%	
Flexural Modulus	2900	MPa	ASTM D790
Impact	Nominal Value	Unit	Test Method
Notched Izod Impact	27	J/m	ASTM D256
Thermal	Nominal Value	Unit	Test Method
Deflection Temperature Under Load (0.45 MPa, Unannealed)	125	°C	ASTM D648

The information and data on this page are provided by manufacturers and document providers. SHANGHAI SUSHENG assumes no legal liability. It is strongly recommended to verify all technical data with material suppliers before final material selection.All rights belong to the original authors. If any infringement occurs, please contact us immediately.

Recommended distributors for this material

Susheng Import & Export Trading Co.,Ltd.

Tel: +86 21 5895 8519
Phone: +86 13424755533
Email: sales@su-jiao.com
No. 215, Lianhe North Road, Fengxian District, Shanghai, China

