# Boda BDF-KR2752

#### Fluoroelastomer

Chenguang Fluoro & Silicone Elastomers Co., Ltd.

### Message:

Material Type: Red color fluoroelastomer compound, hardness Shore A 70-80.

Based on bisphenol curable copolymers.

Features: Excellent mold flow, improved tear resistance and bonding adhesion.

Process Methods: Suitable for compression, transfer and injection molding processes.

Bondability Good Adhesion

Applications: oil seals, steam seals, crank shaft seals and complicated geometries.

Lab Testing Curing Condition: Press Curing: 10min@170°C.

Oven: (8+16)hrs@230°C

General Information

Features

	Good Flow				
	Good Moldability				
	Good Tear Strength				
Uses	Seals				
Appearance	Red				
Processing Method	Compression Molding				
	Injection Molding				
	Resin Transfer Molding				
Physical	Nominal Value	Unit	Test Method		
Specific Gravity	1.92	g/cm³	ASTM D792		
Hardness	Nominal Value	Unit	Test Method		
Durometer Hardness (Shore A)	76		ASTM D2240		
Elastomers	Nominal Value	Unit	Test Method		
Tensile Strength (Yield)	13.5	MPa	ASTM D412		
Tensile Elongation (Break)	270	%	ASTM D412		
Compression Set <sup>1</sup> (200°C, 70 hr)	18	%	ASTM D395		
Aging	Nominal Value	Unit	Test Method		
Change in Tensile Strength in Air (250°C,					
70 hr)	-8.0	%	ASTM D573		
Change in Ultimate Elongation in Air (250°C, 70 hr)	-11	%	ASTM D573		
Change in Durometer Hardness in Air					
(250°C, 70 hr)	2.0		ASTM D573		
Change in Tensile Strength (23°C, 70 hr, in Reference Fuel C)	-11	%	ASTM D471		

Change in Ultimate Elongation (23	°C, 70		
hr, in Reference Fuel C)	-12	%	ASTM D471
Change in Durometer Hardness (23	3°C, 70		
hr, in Reference Fuel C)	-3.0		ASTM D471
Change in Volume (23°C, 70 hr, in			
Reference Fuel C)	4.0	%	ASTM D471
NOTE			
1.	6 mm Buttons		

The information and data on this page are provided by manufacturers and document providers. SHANGHAI SUSHENG assumes no legal liability. It is strongly recommended to verify all technical data with material suppliers before final material selection. All rights belong to the original authors. If any infringement occurs, please contact us immediately.

#### Recommended distributors for this material

## Susheng Import & Export Trading Co.,Ltd.

Tel: +86 21 5895 8519

Phone: +86 13424755533 Email: sales@su-jiao.com

No. 215, Lianhe North Road, Fengxian District, Shanghai, China

