# MFE® -30

### Vinyl Ester

Huachang Polymer Co., Ltd.

### Message:

MFE-30 is a high performance bisphenol-A epoxy vinyl ester resin and has excellent corrosion resistant property.

**PROPERTY** 

Excellent process performance and wet-out with fiber.

Excellent corrosion resistant especially to inorganic acid, alkali and salt.

Excellent mechanical properties, especially resistance to dynamic load.

Low peak exotherm, low shrinkage.

APPLICATION

Various FRP products, especially thick parts.

Can be used in various processes, such as filament winding, pultrusion, spray up, hand lay-up, etc

Applied in engineering projects, such as integral resin mortar flooring, sewing materials, protection layer of metal and concrete structures, etc.

Acid Resistant
Alkali Resistant
Good Corrosion Resistance
Low Exotherm
Low Shrinkage
Salt Water/Spray Resistant
Engineering Parts
Flooring
Yellow
Liquid
Filament Winding
Hand Lay-up
Pultrusion
Spraying

Physical	Nominal Value	Unit	Test Method
Acid Value	7.00 to 13.00	mg KOH/g	
Solids Content	58 to 66	%	
Thermal Stability (80°C)	> 1	day	
Gel Time (25°C)	11.0 to 19.0	min	
Hardness	Nominal Value	Unit	Test Method
Barcol Hardness	45		ASTM D2583
Mechanical	Nominal Value	Unit	Test Method
Tensile Modulus	3600	MPa	ASTM D638
Tensile Strength	90.0	MPa	ASTM D638

Tensile Elongation (Break)	5.8	%	ASTM D638
Flexural Modulus	3400	MPa	ASTM D790
Flexural Strength	150	MPa	ASTM D790
Thermal	Nominal Value	Unit	Test Method
Deflection Temperature Under Load (1.8 MPa, Unannealed)	105	°C	ASTM D648
Thermoset	Nominal Value	Unit	
Thermoset Mix Viscosity (25°C)	350 to 550	сР	

The information and data on this page are provided by manufacturers and document providers. SHANGHAI SUSHENG assumes no legal liability. It is strongly recommended to verify all technical data with material suppliers before final material selection. All rights belong to the original authors. If any infringement occurs, please contact us immediately.

### Recommended distributors for this material

## Susheng Import & Export Trading Co.,Ltd.

Tel: +86 21 5895 8519 Phone: +86 13424755533

Email: sales@su-jiao.com

No. 215, Lianhe North Road, Fengxian District, Shanghai, China

