

Cellophane™ 335LMS

Regenerated Cellulose

Innovia Films Ltd.

Message:

Nitrocellulose Coated Films for Permeable and Barrier Packaging Applications
Transparent, 2 side nitrocellulose coated, heat sealable semi-permeable films
Literature reference: A460

| General Information | | | |
|---|--|--|-----------------|
| Features | Biodegradable | | |
| | General Purpose | | |
| | Heat Sealable | | |
| | High Clarity | | |
| | Renewable Resource Content | | |
| | Semipermeable | | |
| Uses | Film | | |
| | Packaging | | |
| Appearance | Clear/Transparent | | |
| Forms | Film | | |
| Films | Nominal Value | Unit | Test Method |
| Seal Initiation Temperature ¹ (23 µm) | 75.0 to 85.0 | °C | |
| Oxygen Transmission Rate (Wet) (23°C, 23 µm, 0.0% RH) | 3.00 | cm ³ /m ² /24 hr | ASTM F1927 |
| Water Vapor Transmission Rate (23 µm, 38°C, 90% RH) | 600 | g · mm/m ² /atm/24 hr | ASTM E96 |
| Film Gauge | 23.3 | µm | Internal Method |
| Yield (23.3 µm) | 29.9 | m ² /kg | Internal Method |
| NOTE | | | |
| 1. | 0.5 sec dwell, 0.069 MN/m ² | | |

The information and data on this page are provided by manufacturers and document providers. SHANGHAI SUSHENG assumes no legal liability. It is strongly recommended to verify all technical data with material suppliers before final material selection. All rights belong to the original authors. If any infringement occurs, please contact us immediately.

Recommended distributors for this material

Susheng Import & Export Trading Co.,Ltd.

Tel: +86 21 5895 8519

Phone: +86 13424755533

Email: sales@su-jiao.com

No. 215, Lianhe North Road, Fengxian District, Shanghai, China



WECHAT