

Piolen® P G20CA67

Polypropylene Copolymer
PiO Kunststoffe GmbH & Co KG

Message:

Piolen® P G20CA67 is a Polypropylene Copolymer (PP Copolymer) product filled with 20% glass fiber. It can be processed by injection molding and is available in Europe. Applications of Piolen® P G20CA67 include automotive, coating applications and furniture.

Characteristics include:

- Flame Rated
- Chemically Coupled
- Copolymer
- Impact Resistant
- Rigid

General Information			
Filler / Reinforcement	Glass Fiber,20% Filler by Weight		
Features	Chemically Coupled		
	Copolymer		
	Good Flow		
	High Impact Resistance		
	Medium Rigidity		
Uses	Automotive Applications		
	Furniture		
	Protective Coverings		
Appearance	Natural Color		
Forms	Pellets		
Processing Method	Injection Molding		
Physical	Nominal Value	Unit	Test Method
Density	1.04	g/cm³	ISO 1183
Melt Mass-Flow Rate (MFR) (230°C/2.16 kg)	8.5	g/10 min	ISO 1133
Mechanical	Nominal Value	Unit	Test Method
Tensile Stress			ISO 527-2
Yield	57.0	MPa	
Break	56.0	MPa	
Tensile Strain (Break)	5.1	%	ISO 527-2
Flexural Modulus	3480	MPa	ISO 178
Impact	Nominal Value	Unit	Test Method
Charpy Notched Impact Strength			ISO 179/1eA
-40°C	11	kJ/m²	
23°C	16	kJ/m²	
Charpy Unnotched Impact Strength			ISO 179/1eU

-40°C	49	kJ/m ²	
23°C	42	kJ/m ²	
Thermal	Nominal Value	Unit	Test Method
Peak Crystallization Temperature (DSC)	160 to 170	°C	ISO 3146
Flammability	Nominal Value	Test Method	
Flame Rating	HB	UL 94	

The information and data on this page are provided by manufacturers and document providers. SHANGHAI SUSHENG assumes no legal liability. It is strongly recommended to verify all technical data with material suppliers before final material selection. All rights belong to the original authors. If any infringement occurs, please contact us immediately.

Recommended distributors for this material

Susheng Import & Export Trading Co.,Ltd.

Tel: +86 21 5895 8519
 Phone: +86 13424755533
 Email: sales@su-jiao.com
 No. 215, Lianhe North Road, Fengxian District, Shanghai, China

