Geon™ Vinyl Flexible Y126 White 317

Flexible Polyvinyl Chloride

PolyOne Corporation

Message:

Geon™ Vinyl Flexible Y126 White 317 is a Flexible Polyvinyl Chloride product. It can be processed by coextrusion, extrusion, or injection molding and is available in Africa & Middle East, Asia Pacific, Europe, Latin America, or North America.

Characteristics include

Good Adhesion

High Flow

| General Information | | | |
|---|---------------------|-------|-------------|
| Features | Good Adhesion | | |
| | High Flow | | |
| | | | |
| Forms | Pellets | | |
| Processing Method | Coextrusion | | |
| | Extrusion | | |
| | Injection Molding | | |
| | | | |
| Physical | Nominal Value | Unit | Test Method |
| Specific Gravity | 1.20 | g/cm³ | ASTM D792 |
| Hardness | Nominal Value | Unit | Test Method |
| Durometer Hardness (Shore A, 15 sec) | 67 | | ASTM D2240 |
| Mechanical | Nominal Value | Unit | Test Method |
| Tensile Strength ¹ (Break) | 15.2 | MPa | ASTM D638 |
| Tensile Elongation ² (Break) | 400 | % | ASTM D638 |
| Thermal | Nominal Value | Unit | Test Method |
| Brittleness Temperature | -38.9 | °C | ASTM D746 |
| Flammability | Nominal Value | Unit | Test Method |
| Oxygen Index (3.18 mm) | 22 | % | ASTM D2863 |
| Injection | Nominal Value | Unit | |
| Processing (Melt) Temp | 193 to 204 | °C | |
| Extrusion | Nominal Value | Unit | |
| Melt Temperature | 177 to 182 | °C | |
| NOTE | | | |
| 1. | Type IV, 510 mm/min | | |
| 2. | Type IV, 510 mm/min | | |

The information and data on this page are provided by manufacturers and document providers. SHANGHAI SUSHENG assumes no legal liability. It is strongly recommended to verify all technical data with material suppliers before final material selection. All rights belong to the original authors. If any infringement occurs, please contact us immediately.

Susheng Import & Export Trading Co.,Ltd.

Tel: +86 21 5895 8519

Phone: +86 13424755533 Email: sales@su-jiao.com

No. 215, Lianhe North Road, Fengxian District, Shanghai, China

