

SUPRENE® 5890F

Ethylene Propylene Diene Terpolymer
SK Global Chemical

Message:

SUPRENE EPDM 5890F is a non-oil extended grade with very high Mooney viscosity and high ethylene content.
SUPRENE EPDM 5890F is well balanced in processability and physical properties with high loading fillers. Its good green strength can give better shape retention and higher extrudability.
SUPRENE EPDM 5890F is mainly used solid extrudate for automotive parts such as window seal, hose and used in other various applications.

General Information			
Features	Good Processability		
	Good Strength		
	High Viscosity		
Uses	Automotive Applications		
	Automotive Exterior Parts		
	Hose		
	Seals		
Forms	Bale		
Processing Method	Extrusion		
Physical	Nominal Value	Unit	Test Method
Specific Gravity	0.860	g/cm³	ASTM D792
Mooney Viscosity (ML 1+4, 150°C)	64	MU	ASTM D1646
Ethylene Content	68.0	wt%	ASTM D3900
Ethylidene Norbornene (ENB) Content	5.5	wt%	ASTM D6047
Ash Content	0.0100	wt%	ASTM D5667
Volatile Matter	0.20	wt%	ASTM D5668

The information and data on this page are provided by manufacturers and document providers. SHANGHAI SUSHENG assumes no legal liability. It is strongly recommended to verify all technical data with material suppliers before final material selection.All rights belong to the original authors. If any infringement occurs, please contact us immediately.

Recommended distributors for this material

Susheng Import & Export Trading Co.,Ltd.

Tel: +86 21 5895 8519

Phone: +86 13424755533

Email: sales@su-jiao.com

No. 215, Lianhe North Road, Fengxian District, Shanghai, China



WECHAT