

SNOLEN® EB 0.35/46

High Density Polyethylene
JSC Gazprom neftekhim Salavat

Message:

CHARACTERISTIC PROPERTIES
High environmental stress cracking resistance. Good impact strength.
MAJOR APPLICATIONS
Oil tank with heaters. Lange cans. Packing of hazardous consumer goods.

General Information			
Features	Good Impact Resistance		
	High Density		
	High ESCR (Stress Crack Resist.)		
Uses	Packaging		
	Tanks		
Forms	Pellets		
Processing Method	Extrusion Blow Molding		
Physical	Nominal Value	Unit	Test Method
Density (23°C)	0.942 to 0.946	g/cm ³	ISO 1183
Melt Mass-Flow Rate (MFR)			ISO 1133
190°C/21.6 kg	7.0 to 9.0	g/10 min	
190°C/5.0 kg	0.27 to 0.35	g/10 min	
Environmental Stress-Cracking Resistance ¹ (80°C, 2% Arkopal)	15.0	hr	ISO 16770
Melt Flow Ratio	24.0 to 28.0		
Swelling	> 150	%	Internal Method
Hardness	Nominal Value	Unit	Test Method
Shore Hardness (Shore D)	59		ISO 868
Mechanical	Nominal Value	Unit	Test Method
Tensile Modulus - Secant (23°C)	800	MPa	ISO 527-2/1
Tensile Stress			ISO 527-2/50
Yield	21.0	MPa	
Break	34.0	MPa	
Tensile Strain			ISO 527-2/50
Yield	10	%	
Break	> 800	%	
Impact	Nominal Value	Unit	Test Method
Charpy Unnotched Impact Strength (23°C)	17	kJ/m ²	ISO 179
Thermal	Nominal Value	Unit	Test Method

Brittleness Temperature	< -80.0	°C	ASTM D746
Vicat Softening Temperature	80.0	°C	ISO 306/B50
Extrusion	Nominal Value	Unit	
Melt Temperature	180 to 220	°C	
NOTE			
1.	@ 3.5 MPa		

The information and data on this page are provided by manufacturers and document providers. SHANGHAI SUSHENG assumes no legal liability. It is strongly recommended to verify all technical data with material suppliers before final material selection.All rights belong to the original authors. If any infringement occurs, please contact us immediately.

Recommended distributors for this material

Susheng Import & Export Trading Co.,Ltd.

Tel: +86 21 5895 8519
Phone: +86 13424755533
Email: sales@su-jiao.com
No. 215, Lianhe North Road, Fengxian District, Shanghai, China



WECHAT