

ESTABLEND 7500 V0 HF

Polycarbonate + ABS

Cossa Polimeri S.r.l.

Message:

ESTABLEND 7500 V0 HF is a Polycarbonate + ABS (PC+ABS) product. It is available in Europe. Applications of ESTABLEND 7500 V0 HF include automotive, electrical/electronic applications and engineering/industrial parts.

Characteristics include:

- Flame Rated
- Halogen Free
- Flame Retardant
- Good Processability
- Good UV Resistance

General Information			
Features	Bromine Free		
	Chlorine Free		
	Flame Retardant		
	Good Processability		
	Good UV Resistance		
Uses	Automotive Applications		
	Electrical/Electronic Applications		
	Engineering Parts		
Forms	Pellets		
Physical	Nominal Value	Unit	Test Method
Specific Gravity	1.20	g/cm ³	ASTM D792
Melt Mass-Flow Rate (MFR) (240°C/5.0 kg)	25	g/10 min	ASTM D1238
Molding Shrinkage - Flow	0.50 to 0.70	%	ASTM D955
Mechanical	Nominal Value	Unit	Test Method
Tensile Strength			ASTM D638
Yield	60.0	MPa	
Break	54.0	MPa	
Tensile Elongation (Break)	40	%	ASTM D638
Flexural Modulus	2500	MPa	ASTM D790
Impact	Nominal Value	Unit	Test Method
Notched Izod Impact			ASTM D256
0°C	550	J/m	
23°C	600	J/m	
Thermal	Nominal Value	Unit	Test Method
Vicat Softening Temperature			
--	116	°C	ASTM D1525 ¹

--	110	°C	ASTM D1525 ²
Ball Indentation Temperature	105	°C	IEC 60335-1
Flammability	Nominal Value	Unit	Test Method
Flame Rating			UL 94
1.60 mm	V-0		
3.20 mm	V-0		
Glow Wire Ignition Temperature (2.00 mm)	960	°C	IEC 60695-2-13
NOTE			
1.	Rate A (50°C/h), Loading 1 (10 N)		
2.	Rate A (50°C/h), Loading 2 (50 N)		

The information and data on this page are provided by manufacturers and document providers. SHANGHAI SUSHENG assumes no legal liability. It is strongly recommended to verify all technical data with material suppliers before final material selection. All rights belong to the original authors. If any infringement occurs, please contact us immediately.

Recommended distributors for this material

Susheng Import & Export Trading Co.,Ltd.

Tel: +86 21 5895 8519
 Phone: +86 13424755533
 Email: sales@su-jiao.com
 No. 215, Lianhe North Road, Fengxian District, Shanghai, China



WECHAT