

# Xuye J-700C

Chlorinated Polyvinyl Chloride  
Shandong Xuye New Materials Co., Ltd.

Message:

Our company's CPVC resin can be used in the production of extrusion product and injection molding product, especially the production of CPVC tubing and pipe fitting.

General Information			
Uses	Fittings		
	Tubing		
Appearance	Grey		
	Yellow		
Processing Method	Extrusion		
Physical	Nominal Value	Unit	Test Method
Specific Gravity	1.45 to 1.65	g/cm <sup>3</sup>	ASTM D792
Mechanical	Nominal Value	Unit	Test Method
Tensile Modulus	> 2760	MPa	ASTM D638
Tensile Strength (Yield)	> 50.0	MPa	ASTM D638
Impact	Nominal Value	Unit	Test Method
Notched Izod Impact (Area)	> 7.94	kJ/m <sup>2</sup>	ASTM D256
Thermal	Nominal Value	Unit	Test Method
Vicat Softening Temperature	> 110	°C	ASTM D1525 <sup>1</sup>
Flammability	Nominal Value		Test Method
Flame Rating	V-0		UL 94
NOTE			
1.	Loading 2 (50 N)		

The information and data on this page are provided by manufacturers and document providers. SHANGHAI SUSHENG assumes no legal liability. It is strongly recommended to verify all technical data with material suppliers before final material selection. All rights belong to the original authors. If any infringement occurs, please contact us immediately.

Recommended distributors for this material

Susheng Import & Export Trading Co.,Ltd.

Tel: +86 21 5895 8519

Phone: +86 13424755533

Email: sales@su-jiao.com

No. 215, Lianhe North Road, Fengxian District, Shanghai, China



WECHAT