

CAPROWAX P™ 6006-65-NF4140-000

Biodegradable Polymers
POLYFEA

Message:

CAPROWAX P™ 6006-65-NF4140-000 is a Biodegradable Polymers (Biodeg Polymers) product filled with 40% wood fiber. It can be processed by extrusion and is available in Europe. Primary characteristic: eco-friendly/green.

General Information			
Filler / Reinforcement	Wood Fiber,40% Filler by Weight		
Features	Compostable		
	Renewable Resource Content		
Agency Ratings	EN 13432		
Forms	Powder		
Processing Method	Extrusion		
Physical	Nominal Value	Unit	
Apparent Density			
--	0.28	g/cm ³	
-- ¹	0.43	g/cm ³	
Particle Size	< 1.00	mm	
Softening Range	57 to 63	°C	DSC
Residual Moisture Content	< 6.0	%	
Extrusion	Nominal Value	Unit	
Drying Temperature	70.0	°C	
Melt Temperature	100 to 160	°C	
NOTE			
1.	Tapped		

The information and data on this page are provided by manufacturers and document providers. SHANGHAI SUSHENG assumes no legal liability. It is strongly recommended to verify all technical data with material suppliers before final material selection.All rights belong to the original authors. If any infringement occurs, please contact us immediately.

Recommended distributors for this material

Susheng Import & Export Trading Co.,Ltd.

Tel: +86 21 5895 8519

Phone: +86 13424755533

Email: sales@su-jiao.com

No. 215, Lianhe North Road, Fengxian District, Shanghai, China



WECHAT