

INLUBE PPTF20HSLE

Polypropylene
Infinity LTL Engineered Compounds

Message:
20% TEFLO LUBRICATED HEAT STABILIZED POLYPROPYLENE BASED ON FDA COMPLIANT RAW MATERIALS

General Information			
Additive	Heat Stabilizer		
	PTFE Lubricant (20%)		
Features	Food Contact Acceptable		
	Heat Stabilized		
	Lubricated		
Agency Ratings	FDA Unspecified Rating		
Processing Method	Injection Molding		
Physical	Nominal Value	Unit	Test Method
Specific Gravity	1.03	g/cm ³	ASTM D792
Molding Shrinkage - Flow (3.18 mm)	1.8 to 2.3	%	ASTM D955
Water Absorption (Equilibrium)	0.020	%	ASTM D570
Mechanical	Nominal Value	Unit	Test Method
Tensile Strength (Break)	29.0	MPa	ASTM D638
Flexural Modulus	1590	MPa	ASTM D790
Flexural Strength	44.5	MPa	ASTM D790
Impact	Nominal Value	Unit	Test Method
Notched Izod Impact	27	J/m	ASTM D256
Thermal	Nominal Value	Unit	Test Method
Deflection Temperature Under Load (1.8 MPa, Unannealed)	60.0	°C	ASTM D648
Electrical	Nominal Value	Unit	Test Method
Surface Resistivity	1.0E+17	ohms	ASTM D257
Injection	Nominal Value	Unit	
Drying Temperature	76.7	°C	
Drying Time	2.0 to 4.0	hr	
Processing (Melt) Temp	193 to 227	°C	
Mold Temperature	37.8 to 65.6	°C	
Back Pressure	0.345 to 0.689	MPa	
Screw Speed	40 to 70	rpm	

The information and data on this page are provided by manufacturers and document providers. SHANGHAI SUSHENG assumes no legal liability. It is strongly recommended to verify all technical data with material suppliers before final material selection.All rights belong to the original authors. If any infringement occurs, please contact us immediately.

Recommended distributors for this material

Susheng Import & Export Trading Co.,Ltd.

Tel: +86 21 5895 8519

Phone: +86 13424755533

Email: sales@su-jiao.com

No. 215, Lianhe North Road, Fengxian District, Shanghai, China



WECHAT