

TRANSMARE® 44CB70

Polypropylene Copolymer

Transmare Compounding B.V.

Message:

TRANSMARE® 44CB70 is a copolymer polypropylene filled with 70% of barium sulphate.

General Information			
Filler / Reinforcement	Barium Sulfate,70% Filler by Weight		
Features	Copolymer		
Forms	Pellets		
Physical	Nominal Value	Unit	Test Method
Density	2.32	g/cm ³	ISO 1183
Melt Mass-Flow Rate (MFR) (230°C/2.16 kg)	36	g/10 min	ISO 1133
Melt Volume-Flow Rate (MVR) (230°C/2.16 kg)	20.0	cm ³ /10min	ISO 1133
Moisture Content ¹	< 0.20	%	Internal Method
NOTE			
1.	Halogen dryer		

The information and data on this page are provided by manufacturers and document providers. SHANGHAI SUSHENG assumes no legal liability. It is strongly recommended to verify all technical data with material suppliers before final material selection. All rights belong to the original authors. If any infringement occurs, please contact us immediately.

Recommended distributors for this material

Susheng Import & Export Trading Co.,Ltd.

Tel: +86 21 5895 8519

Phone: +86 13424755533

Email: sales@su-jiao.com

No. 215, Lianhe North Road, Fengxian District, Shanghai, China

