

# Generic PAEK - Carbon Fiber

Polyaryletherketone

Generic

## Message:

This data represents typical values that have been calculated from all products classified as: Generic PAEK - Carbon Fiber  
This information is provided for comparative purposes only.

General Information		
Filler / Reinforcement	Carbon fiber reinforced material	
Injection	Nominal Value	Unit
Drying Temperature	149 - 152	°C
Drying Time	3.0 - 8.0	hr
Rear Temperature	365 - 395	°C
Middle Temperature	371 - 400	°C
Front Temperature	377 - 406	°C
Mold Temperature	163 - 184	°C
Injection instructions		

This data represents typical values that have been calculated from all products classified as: Generic PAEK - Carbon FiberThis information is provided for comparative purposes only.

The information and data on this page are provided by manufacturers and document providers. SHANGHAI SUSHENG assumes no legal liability. It is strongly recommended to verify all technical data with material suppliers before final material selection.All rights belong to the original authors. If any infringement occurs, please contact us immediately.

## Recommended distributors for this material

### Susheng Import & Export Trading Co.,Ltd.

Tel: +86 21 5895 8519  
Phone: +86 13424755533  
Email: sales@su-jiao.com  
No. 215, Lianhe North Road, Fengxian District, Shanghai, China

