

ESTOPLAST EP 4140GY11

Polybutylene Terephthalate

Ester Industries Ltd.

Message:

Polybutylene Terephthalate - 40% Glass /Mineral filled,Flame retardant, Grey
Electrical & Electronic: CFL /LED /Tubelight accessories

General Information			
Filler / Reinforcement	Glass \mineral, 40% filler by weight		
Additive	demoulding		
	UV stabilizer		
	Flame retardancy		
Features	UV Stabilized		
	Heat conduction		
	Halogenated		
	Good demoulding performance		
	Flame retardancy		
Uses	Electrical/Electronic Applications		
RoHS Compliance	RoHS compliance		
Appearance	Grey		
Forms	Particle		
Processing Method	Injection molding		
Physical	Nominal Value	Unit	Test Method
Density	1.85	g/cm ³	ISO 1183
Mechanical	Nominal Value	Unit	Test Method
Tensile Strength	80.0	MPa	ASTM D638
Tensile Elongation (Break)	2.5	%	ASTM D638
Flexural Strength	110	MPa	ASTM D790
Impact	Nominal Value	Unit	Test Method
Notched Izod Impact	50	J/m	ASTM D256
Thermal	Nominal Value	Unit	Test Method
Deflection Temperature Under Load (0.45 MPa, Unannealed)	210	°C	ASTM D648
Flammability	Nominal Value		Test Method
Flame Rating (1.5 mm)	V-0		UL 94
Injection	Nominal Value	Unit	
Drying Temperature	110 - 120	°C	
Drying Time	3.0 - 4.0	hr	
Rear Temperature	235 - 240	°C	

Middle Temperature	250 - 260	°C
Nozzle Temperature	250 - 260	°C
Processing (Melt) Temp	240 - 250	°C
Mold Temperature	90 - 110	°C

The information and data on this page are provided by manufacturers and document providers. SHANGHAI SUSHENG assumes no legal liability. It is strongly recommended to verify all technical data with material suppliers before final material selection. All rights belong to the original authors. If any infringement occurs, please contact us immediately.

Recommended distributors for this material

Susheng Import & Export Trading Co.,Ltd.

Tel: +86 21 5895 8519
Phone: +86 13424755533
Email: sales@su-jiao.com
No. 215, Lianhe North Road, Fengxian District, Shanghai, China

