Polylink Polymer P-11020-GF

Compounded Polypropylene Polylink Polymers (India) Ltd.

Message:

Filled Polypropylene compounds are manufactured by compounding Polypropylene with fine fillers (i.e. mica, chalk, talc, glass). Additives like antioxidants, lubricant, processing aid and desiccant are added to improve long term thermal and processability. The compounds used directly or diluted with desired grades of polypropylenes show good dispensability and excellent balance of properties in the ultimate product. The fillers in the compound incorporates certain important properties those are essential for ultimate product. The modification are as below.

| General Information | | | |
|--------------------------|-----------------------------------|-------|-----------------|
| Filler / Reinforcement | Glass \mica, 18% filler by weight | | |
| Features | Homopolymer | | |
| Processing Method | Extrusion | | |
| Physical | Nominal Value | Unit | Test Method |
| Density | 1.05 - 1.10 | g/cm³ | Internal method |
| Moisture Content | < 800 | ppm | Internal method |
| Mechanical | Nominal Value | Unit | Test Method |
| Tensile Strength (Break) | 34.3 - 39.2 | MPa | ASTM D638 |
| Flexural Modulus | 4120 - 4310 | MPa | ASTM D790 |
| Flexural Strength | 49.0 - 63.7 | MPa | ASTM D790 |
| Impact | Nominal Value | Unit | Test Method |
| Notched Izod Impact | 64 - 69 | J/m | ASTM D256 |
| Extrusion | Nominal Value | Unit | |
| Drying Temperature | 70.0 | °C | |
| Drying Time | 0.50 | hr | |
| Cylinder Zone 1 Temp. | 190 | °C | |
| Cylinder Zone 2 Temp. | 200 | °C | |
| Cylinder Zone 3 Temp. | 210 | °C | |
| Cylinder Zone 4 Temp. | 215 | °C | |
| Cylinder Zone 5 Temp. | 220 | °C | |

Zone 6: 230°C

The information and data on this page are provided by manufacturers and document providers. SHANGHAI SUSHENG assumes no legal liability. It is strongly recommended to verify all technical data with material suppliers before final material selection. All rights belong to the original authors. If any infringement occurs, please contact us immediately.

Recommended distributors for this material

Susheng Import & Export Trading Co.,Ltd.

Tel: +86 21 5895 8519 Phone: +86 13424755533 Email: sales@su-jiao.com No. 215, Lianhe North Road, Fengxian District, Shanghai, China

