

Hostacom HBG H01 BLACK

Polypropylene Homopolymer
LyondellBasell Industries

Message:

Hostacom HBG H01 BLACK is a 10% glass fiber reinforced PP homopolymer, with low flowability and high LTHS (long term heat stability). The product is also available in black color, pellet form.
This grade is not intended for medical, pharmaceutical, food and drinking water applications.

General Information			
Filler / Reinforcement	Glass fiber reinforced material, 10% filler by weight		
Features	Homopolymer		
	Good heat aging resistance		
	Low liquidity		
Uses	Water tank		
Appearance	Black		
Forms	Particle		
Processing Method	Injection molding		
Physical	Nominal Value	Unit	Test Method
Density (23°C)	0.980	g/cm ³	ISO 1183/A
Melt Mass-Flow Rate (MFR) (230°C/5.0 kg)	2.0	g/10 min	ISO 1133
Melt Volume-Flow Rate (MVR) (230°C/5.0 kg)	2.50	cm ³ /10min	ISO 1133
Mechanical	Nominal Value	Unit	Test Method
Tensile Modulus (23°C)	2600	MPa	ISO 527-2
Tensile Stress (Yield, 23°C)	50.0	MPa	ISO 527-2
Tensile Strain (Break)	8.0	%	ISO 527-2
Impact	Nominal Value	Unit	Test Method
Charpy Notched Impact Strength (23°C)	9.5	kJ/m ²	ISO 179/1eA
Charpy Unnotched Impact Strength (23°C)	47	kJ/m ²	ISO 179/1eU
Thermal	Nominal Value	Unit	Test Method
Heat Deflection Temperature			
0.45 MPa, not annealed	140	°C	ISO 75-2/B
1.8 MPa, not annealed	90.0	°C	ISO 75-2/A
Vicat Softening Temperature	110	°C	ISO 306/B

The information and data on this page are provided by manufacturers and document providers. SHANGHAI SUSHENG assumes no legal liability. It is strongly recommended to verify all technical data with material suppliers before final material selection.All rights belong to the original authors. If any infringement occurs, please contact us immediately.

Recommended distributors for this material

Susheng Import & Export Trading Co.,Ltd.

Tel: +86 21 5895 8519

Phone: +86 13424755533

Email: sales@su-jiao.com

No. 215, Lianhe North Road, Fengxian District, Shanghai, China

