

POCAN® A 3131 000000

Polybutylene Terephthalate + ASA

LANXESS Corporation

Message:

PBT+ASA, 30 % glass fibers, injection molding, low tendency to warp, improved surface finish

General Information			
Filler / Reinforcement	Glass Fiber,30% Filler by Weight		
Features	Good Surface Finish		
	Low Warpage		
Processing Method	Injection Molding		
Physical	Nominal Value	Unit	Test Method
Density (23°C)	1.50	g/cm ³	ISO 1183
Apparent Density	0.85	g/cm ³	ISO 60
Melt Volume-Flow Rate (MVR) (270°C/5.0 kg)	40.0	cm ³ /10min	ISO 1133
Molding Shrinkage			ISO 294-4
Across Flow : 270°C, 2.00 mm ¹	0.80	%	
Across Flow : 120°C, 2 hr, 2.00 mm ²	0.10	%	
Flow : 270°C, 2.00 mm ³	0.30	%	
Flow : 120°C, 2 hr, 2.00 mm ⁴	0.10	%	
Water Absorption			ISO 62
Saturation, 23°C	0.40	%	
Equilibrium, 23°C, 50% RH	0.10	%	
Mechanical	Nominal Value	Unit	Test Method
Tensile Modulus (23°C)	9800	MPa	ISO 527-2/1
Tensile Stress (Break, 23°C)	135	MPa	ISO 527-2/5
Tensile Strain (Break, 23°C)	2.4	%	ISO 527-2/5
Flexural Modulus ⁵ (23°C)	9700	MPa	ISO 178/A
Flexural Stress ⁶ (23°C)	200	MPa	ISO 178
Flexural Strain at Flexural Strength ⁷ (23°C)	2.7	%	
ISO Shortname	PBT+PET+ASA, GHMR, 07-100, GF30		ISO 7792
Residual Moisture Content	0.0 to 0.020	%	Karl Fisher
Impact	Nominal Value	Unit	Test Method
Charpy Notched Impact Strength			ISO 179/1eA
-30°C	< 10	kJ/m ²	
23°C	< 10	kJ/m ²	
Charpy Unnotched Impact Strength			ISO 179/1eU
-30°C	55	kJ/m ²	

23°C	55	kJ/m ²	
Notched Izod Impact Strength			ISO 180/1A
-30°C	< 10	kJ/m ²	
23°C	< 10	kJ/m ²	
Unnotched Izod Impact Strength			ISO 180/1U
-30°C	50	kJ/m ²	
23°C	50	kJ/m ²	
Thermal	Nominal Value	Unit	Test Method
Heat Deflection Temperature			
0.45 MPa, Unannealed	220	°C	ISO 75-2/B
1.8 MPa, Unannealed	185	°C	ISO 75-2/A
Vicat Softening Temperature	175	°C	ISO 306/B120
Melting Temperature ⁸	225 to 250	°C	ISO 11357-3
CLTE			ISO 11359-2
Flow : 23 to 55°C	2.0E-5	cm/cm/°C	
Transverse : 23 to 55°C	1.0E-4	cm/cm/°C	
Electrical	Nominal Value	Unit	Test Method
Comparative Tracking Index (Solution A)	300	V	IEC 60112
Flammability	Nominal Value	Unit	Test Method
Flame Rating			UL 94
0.800 mm	HB		
1.60 mm	HB		
Injection	Nominal Value	Unit	Test Method
Drying Temperature - Circulation Dryer	120	°C	
Drying Time - Circulation Dryer	4.0 to 8.0	hr	
Processing (Melt) Temp	260 to 280	°C	
Mold Temperature	80.0 to 100	°C	
NOTE			
1.	60x60x2; MT 90°C; 600 Bar		
2.	60x60x2		
3.	60x60x2; MT 90°C; 600 Bar		
4.	60x60x2		
5.	2.0 mm/min		
6.	2.0 mm/min		
7.	Pull Rate: 2 mm/min; 50% RH		
8.	10°C/min		

The information and data on this page are provided by manufacturers and document providers. SHANGHAI SUSHENG assumes no legal liability. It is strongly recommended to verify all technical data with material suppliers before final material selection. All rights belong to the original authors. If any infringement occurs, please contact us immediately.

Recommended distributors for this material

Susheng Import & Export Trading Co.,Ltd.

Tel: +86 21 5895 8519

Phone: +86 13424755533

Email: sales@su-jiao.com

No. 215, Lianhe North Road, Fengxian District, Shanghai, China

