Yuyao PA 033ML20

Polyamide 66/6 Copolymer

Yuyao Tenglong Plastics Co., Ltd.

Message:

Yuyao PA 033ML20 is a Polyamide 66/6 Copolymer (Nylon 66/6) product. It can be processed by injection molding and is available in Asia Pacific. Applications of Yuyao PA 033ML20 include electrical/electronic applications, appliances, automotive and tools.

Characteristics include:

Flame Rated

Flame Retardant

Good Processability

General Information

Halogen Free

Heat Resistant

Additive	Flame Retardant			
Features	Flame Retardant			
	Good Electrical Properties			
	Good Processability			
	Halogen Free			
	High Heat Resistance			
	High Strength			
Uses	Appliance Components			
	Automotive Under the Hood			
	Communication Applications			
	Computer Components			
	Connectors			
	Electrical Parts			
	Power/Other Tools			
Processing Method	Injection Molding			
Physical	Nominal Value	Unit	Test Method	
Specific Gravity	1.28	g/cm³	ASTM D792	
Molding Shrinkage - Flow	0.50 to 0.80	%	ASTM D955	
Mechanical	Nominal Value	Unit	Test Method	
Tensile Strength	130	MPa	ASTM D638	
Tensile Elongation (Break)	5.5	%	ASTM D638	
Flexural Modulus	5100	МРа	ASTM D790	
Flexural Strength	160	МРа	ASTM D790	
Impact	Nominal Value	Unit	Test Method	
Notched Izod Impact (Area)	11.0	kJ/m²	ASTM D256	
Thermal	Nominal Value	Unit	Test Method	

Deflection Temperature Under Load (1.8			
MPa, Unannealed)	200	°C	ASTM D648
Electrical	Nominal Value	Unit	Test Method
Volume Resistivity	1.0E+15	ohms·cm	ASTM D257
Flammability	Nominal Value	Unit	Test Method
Flame Rating			UL 94
1.60 mm	V-0		
3.20 mm	V-0		
Injection	Nominal Value	Unit	
Drying Temperature	90.0 to 95.0	°C	
Drying Time	5.0 to 8.0	hr	
Processing (Melt) Temp	220 to 270	°C	
Mold Temperature	40.0 to 80.0	°C	
Injection Pressure	80.0 to 100	MPa	

The information and data on this page are provided by manufacturers and document providers. SHANGHAI SUSHENG assumes no legal liability. It is strongly recommended to verify all technical data with material suppliers before final material selection. All rights belong to the original authors. If any infringement occurs, please contact us immediately.

Recommended distributors for this material

Susheng Import & Export Trading Co.,Ltd.

Tel: +86 21 5895 8519 Phone: +86 13424755533 Email: sales@su-jiao.com

No. 215, Lianhe North Road, Fengxian District, Shanghai, China

