

Generic PEI - Glass Fiber, Milled

Polyether Imide

Generic

Message:

This data represents typical values that have been calculated from all products classified as: Generic PEI - Glass Fiber, Milled
This information is provided for comparative purposes only.

General Information			
Filler / Reinforcement	Milled Glass Fiber		
Physical	Nominal Value	Unit	Test Method
Molding Shrinkage - Flow (23°C)	0.35 to 0.60	%	ASTM D955
Mechanical	Nominal Value	Unit	Test Method
Flexural Modulus (23°C)	5100 to 6550	MPa	ASTM D790
Thermal	Nominal Value	Unit	Test Method
Deflection Temperature Under Load (1.8 MPa, Unannealed)	199 to 208	°C	ASTM D648

The information and data on this page are provided by manufacturers and document providers. SHANGHAI SUSHENG assumes no legal liability. It is strongly recommended to verify all technical data with material suppliers before final material selection.All rights belong to the original authors. If any infringement occurs, please contact us immediately.

Recommended distributors for this material


Susheng Import & Export Trading Co.,Ltd.

Tel: +86 21 5895 8519

Phone: +86 13424755533

Email: sales@su-jiao.com

No. 215, Lianhe North Road, Fengxian District, Shanghai, China



WECHAT