

# CONTINUUM™ DGDA-2492 BK

Bimodal Polyethylene Resin  
The Dow Chemical Company

Message:

CONTINUUM™ DGDA-2492 BK Bimodal Polyethylene Resin is produced using UNIPOL™ II process technology. This product may be utilized for pipe applications where long-term hydrostatic strength combined with outstanding resistance to slow crack growth, rapid crack propagation, and high melt strength is desired. Suitable applications include natural gas distribution pipes, large diameter industrial piping, mining, sewage, and municipal water service lines.

Industrial Standards Compliance:

ASTM D 3350: cell classification

Black - PE445576C (MRS) (See notes 1)

Black - PE445574C (HDB) (See notes 1)

Plastics Pipe Institute (PPI): TR-4

Black Pipe - CONTINUUM™ DGDA-2492 BK (See Notes 1)

ISO PE100 pipe grade - MRS 10 @ 20°C; CRS 6.3 @ 60°C, 11 yr

ASTM PE4710 pipe grade - 1600psi HDB and 1000psi HDS @ 73°F, 1000psi HDB @ 140°F

NSF International: Standard 14 and 61

Black Pipe - DGDA-2492 BK<sup>3</sup>

ASME

Code Case N755

Consult the regulations for complete details.

Notes:

(1) Compression molded parts prepared according to ASTM D 4703 Procedure C unless otherwise noted in the test method. Properties will vary with changes in molding conditions and aging time.

General Information			
Additive	Processing Aid		
Agency Ratings	ASTM D 3350 PE445574C		
	ASTM D 3350 PE445576C		
	ASTM PE4710		
	ISO PE 100		
	NSF 14		
	NSF 61		
	PPI TR-4		
Forms	Pellets		
Processing Method	Profile Extrusion		
Physical	Nominal Value	Unit	Test Method
Density			ASTM D1505
Natural	0.949	g/cm <sup>3</sup>	
Black <sup>1</sup>	0.959	g/cm <sup>3</sup>	
Melt Mass-Flow Rate (MFR)			ASTM D1238
190°C/2.16 kg	0.060	g/10 min	
190°C/21.6 kg	6.5	g/10 min	
Mechanical	Nominal Value	Unit	Test Method
Tensile Strength <sup>2</sup> (Yield)	> 24.1	MPa	ASTM D638

Tensile Elongation <sup>3</sup> (Break)	> 500	%	ASTM D638
Flexural Modulus	1030	MPa	ASTM D790B
Creep Rupture Strength - 1798 psi (12.4 MPa) (20°C)	> 200	hr	ISO 1167
Hydrostatic Strength			ASTM D1598
1798 psi (12.4 MPa) : 20°C	> 100	hr	
725 psi (5.0 MPa) : 80°C	> 1000	hr	
Resistance to Rapid Crack Propagation, Pc <sub>4</sub>			
Calculated, Full Scale (@32°F) : 0°C	> 46.0	bar	ISO 13478
S-4 (@32°F) : -18°C	> 12.0	bar	ISO 13477
Resistance to Rapid Crack Propagation, Tc - S-4 Tc (@ 12 bar) <sup>5</sup>	< -18	°C	ISO 13477
Slow Crack Growth PENT <sup>6</sup>	> 10000	hr	ASTM F1473
Thermal Stability	> 220	°C	ASTM D3350
Impact	Nominal Value	Unit	Test Method
Notched Izod Impact <sup>7</sup> (23°C)	490	J/m	ASTM D256A
Thermal	Nominal Value	Unit	Test Method
Brittleness Temperature	< -75.0	°C	ASTM D7426
NOTE			

1.

Natural resin extruded under proper conditions with carbon black masterbatch DFNF-0092 (6.5%).

2.

Compression molded parts prepared according to ASTM D 4703 Procedure C unless otherwise noted in the test method. Properties will vary with changes in molding conditions and aging time.

3.

Compression molded parts prepared according to ASTM D 4703 Procedure C unless otherwise noted in the test method. Properties will vary with changes in molding conditions and aging time.

4.

Pipe diameter of 10 inch IPS (25.4 cm) and Standard Diameter Ratio (SDR) 11.

5.

Pipe diameter of 10 inch IPS (25.4 cm) and Standard Diameter Ratio (SDR) 11.

6.

Compression molded parts prepared according to ASTM D 4703 Procedure C unless otherwise noted in the test method. Properties will vary with changes in molding conditions and aging time.

7.

Compression molded parts  
prepared according to ASTM D  
4703 Procedure C unless otherwise  
noted in the test method.  
Properties will vary with changes in  
molding conditions and aging  
time.

The information and data on this page are provided by manufacturers and document providers. SHANGHAI SUSHENG assumes no legal liability. It is strongly recommended to verify all technical data with material suppliers before final material selection. All rights belong to the original authors. If any infringement occurs, please contact us immediately.

#### Recommended distributors for this material

### Susheng Import & Export Trading Co.,Ltd.

Tel: +86 21 5895 8519

Phone: +86 13424755533

Email: sales@su-jiao.com

No. 215, Lianhe North Road, Fengxian District, Shanghai, China

