

Comco PA 6 G high impact

Polyamide 6
Comco-Plastic GmbH

Message:

Comco PA 6 G high impact is a Polyamide 6 (Nylon 6) material. It is available in Europe.
Important attributes of Comco PA 6 G high impact are:
Flame Rated
Impact Resistant

General Information				
Features		High Impact Resistance		
Appearance		Natural Color		
Physical	Dry	Conditioned	Unit	Test Method
Density	1.13	--	g/cm ³	ISO 1183
Water Absorption				
Saturation, 23°C	6.0	--	%	
Equilibrium, 23°C, 50% RH	1.8	--	%	
Water Absorption				ISO 62
after 24 h immersion in water : 23°C	40.0	--	mg	
after 96 h immersion in water : 23°C	79.0	--	mg	
Maximum Service Temperature				
in air continuously	105	--	°C	
in air for short periods	170	--	°C	
Service Temperature - Minimum				
	-30	--	°C	
Hardness	Dry	Conditioned	Unit	Test Method
Rockwell Hardness (M-Scale)	88	--		ISO 2039-2
Shore Hardness (Shore D)	80	--		ISO 868
Ball Indentation Hardness	165	--	MPa	ISO 2039-1
Mechanical	Dry	Conditioned	Unit	Test Method
Tensile Modulus (23°C)	2600	--	MPa	ISO 527-2
Tensile Stress (Yield, 23°C)	68.0	45.0	MPa	ISO 527-2
Tensile Strain (Break, 23°C)	25	> 50	%	ISO 527-2
Compressive Stress (1% Strain)	26.0	--	MPa	ISO 604
Impact	Dry	Conditioned	Unit	Test Method
Charpy Notched Impact Strength	3.5	--	kJ/m ²	ISO 179/1eA

Charpy Unnotched Impact Strength	No Break	--		ISO 179/1eU
Notched Izod Impact Strength	3.5	7.0	kJ/m ²	ISO 180/2A
Thermal	Dry	Conditioned	Unit	Test Method
Heat Deflection Temperature (1.8 MPa, Unannealed)	80.0	--	°C	ISO 75-2/A
Melting Temperature	220	--	°C	
CLTE - Flow				
23 to 60°C	8.0E-5	--	cm/cm/°C	
23 to 100°C	9.0E-5	--	cm/cm/°C	
Thermal Conductivity	0.25	--	W/m/K	
Electrical	Dry	Conditioned	Unit	Test Method
Surface Resistivity	> 1.0E+13	> 1.0E+12	ohms	IEC 60093
Volume Resistivity	> 1.0E+14	> 1.0E+12	ohms·cm	IEC 60093
Electric Strength	25	17	kV/mm	IEC 60243-1
Relative Permittivity				IEC 60250
100 Hz	3.60	6.60		
1 MHz	3.20	3.70		
Dissipation Factor				IEC 60250
100 Hz	0.012	0.14		
1 MHz	0.016	0.050		
Comparative Tracking Index	600	600	V	IEC 60112
Flammability	Dry	Conditioned	Unit	Test Method
Flame Rating				UL 94
3.00 mm	HB	--		
6.00 mm	HB	--		

The information and data on this page are provided by manufacturers and document providers. SHANGHAI SUSHENG assumes no legal liability. It is strongly recommended to verify all technical data with material suppliers before final material selection. All rights belong to the original authors. If any infringement occurs, please contact us immediately.

Recommended distributors for this material

Susheng Import & Export Trading Co.,Ltd.

Tel: +86 21 5895 8519

Phone: +86 13424755533

Email: sales@su-jiao.com

No. 215, Lianhe North Road, Fengxian District, Shanghai, China



WECHAT