

FARALLOY® PP-155

Polypropylene

O'Neil Color and Compounding

Message:

FARALLOY PP-155 is an injection moldable grade polypropylene formulated to resist ignition as defined by Underwriters' Laboratories 94V test protocol.

General Information			
Additive	Flame Retardant		
Features	Flame Retardant		
	Ignition Resistant		
Forms	Pellets		
Processing Method	Injection Molding		
Physical	Nominal Value	Unit	Test Method
Specific Gravity	1.23	g/cm ³	ASTM D792
Melt Mass-Flow Rate (MFR) (230°C/2.16 kg)	8.0	g/10 min	ASTM D1238
Mechanical	Nominal Value	Unit	Test Method
Tensile Strength	16.2	MPa	ASTM D638
Tensile Elongation (Break)	21	%	ASTM D638
Flexural Modulus	1050	MPa	ASTM D790
Flexural Strength	26.2	MPa	ASTM D790
Impact	Nominal Value	Unit	Test Method
Notched Izod Impact	130	J/m	ASTM D256
Thermal	Nominal Value	Unit	Test Method
Deflection Temperature Under Load (0.45 MPa, Annealed)	85.6	°C	ASTM D648
Flammability	Nominal Value		Test Method
Flame Rating (1.59 mm)	V-0		UL 94

The information and data on this page are provided by manufacturers and document providers. SHANGHAI SUSHENG assumes no legal liability. It is strongly recommended to verify all technical data with material suppliers before final material selection. All rights belong to the original authors. If any infringement occurs, please contact us immediately.

Recommended distributors for this material

Susheng Import & Export Trading Co.,Ltd.

Tel: +86 21 5895 8519

Phone: +86 13424755533

Email: sales@su-jiao.com

No. 215, Lianhe North Road, Fengxian District, Shanghai, China



WECHAT