

VESTAKEEP® 4000P

Polyetheretherketone

Evonik Industries AG

Message:

Unreinforced, high-viscosity polyether ether ketone fine powder.
VESTAKEEP 4000P is an unreinforced, high-viscosity polyether ether ketone fine powder. The product is suitable for the manufacture of compounds or it can be used as scatterpowder for the manufacture of composites.
The semi-crystalline polymer features superior thermal and chemical resistance. VESTAKEEP 4000P is self-extinguishing.

General Information			
Features	Good Chemical Resistance		
	High Viscosity		
	Self Extinguishing		
	Semi Crystalline		
Forms	Powder		
Physical	Nominal Value	Unit	Test Method
Density	1.30	g/cm ³	ISO 1183
Apparent Density	0.22	g/cm ³	ISO 60
Melt Volume-Flow Rate (MVR) (380°C/5.0 kg)	11.0	cm ³ /10min	ISO 1133
Average Particle Size - d50 ¹	550	µm	
Mechanical	Nominal Value	Unit	Test Method
Tensile Modulus	3500	MPa	ISO 527-2
Tensile Stress (Yield)	96.0	MPa	ISO 527-2
Tensile Strain			ISO 527-2
Yield	5.0	%	
Break	30	%	
Impact	Nominal Value	Unit	Test Method
Charpy Notched Impact Strength			ISO 179/1eA
-30°C, Complete Break	6.0	kJ/m ²	
23°C, Complete Break	7.0	kJ/m ²	
Charpy Unnotched Impact Strength			ISO 179/1eU
-30°C	No Break		
23°C	No Break		
Thermal	Nominal Value	Unit	Test Method
Heat Deflection Temperature			
0.45 MPa, Unannealed	205	°C	ISO 75-2/B
1.8 MPa, Unannealed	150	°C	ISO 75-2/A
Vicat Softening Temperature			
--	335	°C	ISO 306/A

--	305	°C	ISO 306/B
Melting Temperature ²	340	°C	ISO 11357-3
Flammability	Nominal Value		Test Method
Flame Rating (3.20 mm)	V-0		UL 94
NOTE			
1.	Malvern Mastersizer		
2.	2nd heating		

The information and data on this page are provided by manufacturers and document providers. SHANGHAI SUSHENG assumes no legal liability. It is strongly recommended to verify all technical data with material suppliers before final material selection. All rights belong to the original authors. If any infringement occurs, please contact us immediately.

Recommended distributors for this material

Susheng Import & Export Trading Co.,Ltd.

Tel: +86 21 5895 8519

Phone: +86 13424755533

Email: sales@su-jiao.com

No. 215, Lianhe North Road, Fengxian District, Shanghai, China

