

NORYL GTX™ GTX951W resin

Polyphenylene Ether + PS + Nylon

SABIC Innovative Plastics Asia Pacific

Message:

A new high flow GTX designed for under-the-hood applications such as power distribution boxes, relay boxes and junction boxes. Developmental name EXNX0151.

General Information			
Features	High liquidity		
Uses	Parts under the hood of a car		
RoHS Compliance	RoHS compliance		
Physical	Nominal Value	Unit	Test Method
Specific Gravity	1.10	g/cm ³	ASTM D792
Melt Mass-Flow Rate (MFR)			ASTM D1238
280°C/2.16 kg	23	g/10 min	ASTM D1238
280°C/5.0 kg	64	g/10 min	ASTM D1238
Molding Shrinkage			ASTM D955
Flow: 24 hours	1.4 - 1.7	%	ASTM D955
Transverse flow: 24 hours	1.2 - 1.5	%	ASTM D955
Water Absorption			ISO 62
23°C, 24 hr	2.0	%	ISO 62
23°C, 24 hr ¹	0.39	%	ISO 62
Mechanical	Nominal Value	Unit	Test Method
Tensile Modulus ²	2250	MPa	ASTM D638
Tensile Strength			
Yield ³	66.0	MPa	ASTM D638
Yield	66.0	MPa	ISO 527-2/50
Fracture ⁴	57.0	MPa	ASTM D638
Tensile Elongation			
Yield ⁵	5.0	%	ASTM D638
Fracture ⁶	55	%	ASTM D638
Fracture	51	%	ISO 527-2/50
Flexural Modulus			
100mm span ⁷	2550	MPa	ASTM D790
-- ⁸	2380	MPa	ISO 178
Flexural Stress			
--	98.0	MPa	ISO 178
Fracture, 100mm span ⁹	100	MPa	ASTM D790
Impact	Nominal Value	Unit	Test Method
Charpy Notched Impact Strength			ISO 179/2C

-20°C	11	kJ/m ²	ISO 179/2C
23°C	21	kJ/m ²	ISO 179/2C
Notched Izod Impact			
-30°C	100	J/m	ASTM D256
23°C	210	J/m	ASTM D256
-30°C ¹⁰	8.1	kJ/m ²	ISO 180/4A
23°C ¹¹	14	kJ/m ²	ISO 180/4A
Instrumented Dart Impact			ASTM D3763
-30°C, Energy at Peak Load	32.0	J	ASTM D3763
23°C, Energy at Peak Load	48.0	J	ASTM D3763
Thermal	Nominal Value	Unit	Test Method
Deflection Temperature Under Load			
0.45 MPa, unannealed, 6.40mm	196	°C	ASTM D648
0.45 MPa, unannealed, 100 mm span ¹²	181	°C	ISO 75-2/Be
Linear thermal expansion coefficient			ASTM E831
Flow: -40 to 40°C	9.0E-5	cm/cm/°C	ASTM E831
Flow: 60 to 138°C	1.7E-4	cm/cm/°C	ASTM E831
Lateral: -40 to 40°C	8.5E-5	cm/cm/°C	ASTM E831
Horizontal: 60 to 138°C	1.5E-4	cm/cm/°C	ASTM E831
Electrical	Nominal Value	Unit	Test Method
Dielectric Strength (1.60 mm, in Oil)	22	kV/mm	ASTM D149
Dissipation Factor (1 MHz)	0.017		ASTM D150
NOTE			
1.	50% RH		
2.	50 mm/min		
3.	Type 1, 50mm/min		
4.	Type 1, 50mm/min		
5.	Type 1, 50mm/min		
6.	Type 1, 50mm/min		
7.	2.6 mm/min		
8.	2.0 mm/min		
9.	2.6 mm/min		
10.	63.5*12.7*3.2		
11.	63.5*12.7*3.2		
12.	120*10*4 mm		

The information and data on this page are provided by manufacturers and document providers. SHANGHAI SUSHENG assumes no legal liability. It is strongly recommended to verify all technical data with material suppliers before final material selection. All rights belong to the original authors. If any infringement occurs, please contact us immediately.

Recommended distributors for this material

Susheng Import & Export Trading Co.,Ltd.

Tel: +86 21 5895 8519

Phone: +86 13424755533

Email: sales@su-jiao.com

No. 215, Lianhe North Road, Fengxian District, Shanghai, China

