

# Xuchuan A-9080W/B-6088

Thermoplastic Polyurethane Elastomer (Polyester)

Xuchuan Chemical (Suzhou) Co., Ltd

## Message:

Xuchuan A-9080W/B-6088 is a Thermoplastic Polyurethane Elastomer (Polyester) (TPU-Polyester) product. It is available in Asia Pacific. Typical application: Consumer Goods.

Characteristics include:

Good Aesthetics

High Hardness

General Information		
Features	High Hardness	
	Low Density	
	Pleasing Surface Appearance	
Uses	Footwear	
Physical	Nominal Value	Unit
Density	0.350 to 0.600	g/cm <sup>3</sup>
Density		
A-9080W : 40°C	1.010 to 1.020	g/cm <sup>3</sup>
B-6088 : 40°C	1.080 to 1.200	g/cm <sup>3</sup>
Viscosity		
A-9080W : 40°C	1.00 to 1.30	Pa·s
B-6088 : 40°C	0.600 to 0.800	Pa·s
Williams Abrasion	130 to 200	cc/php
Cream Time	6.0 to 8.0	sec
End of Rise Time	30.0 to 40.0	sec
Free Rise Foam Density	210 to 260	kg/m <sup>3</sup>
Preheat Temperature		
Part A	50 to 60	°C
Part B	50 to 60	°C
Preheat Time		
Part A	6.0 to 8.0	hr
Part B	6.0 to 8.0	hr
Processing Temperature		
Part A	40 to 45	°C
Part B	38 to 42	°C
Hardness	Nominal Value	Unit
Durometer Hardness (Shore A)	60 to 88	
Elastomers	Nominal Value	Unit
Tensile Strength (Break)	4.00 to 7.00	MPa

Tensile Elongation (Break)	200 to 300	%
Tear Strength	11.0 to 20.0	kN/m
Thermoset	Nominal Value	Unit
Thermoset Components		
Part A	Mix Ratio by Weight: 100	
Part B	Mix Ratio by Weight: 100	
Demold Time	5.0 to 7.0	min
Injection	Nominal Value	Unit
Mold Temperature	45.0 to 55.0	°C

The information and data on this page are provided by manufacturers and document providers. SHANGHAI SUSHENG assumes no legal liability. It is strongly recommended to verify all technical data with material suppliers before final material selection. All rights belong to the original authors. If any infringement occurs, please contact us immediately.

Recommended distributors for this material

## Susheng Import & Export Trading Co.,Ltd.

Tel: +86 21 5895 8519  
 Phone: +86 13424755533  
 Email: sales@su-jiao.com  
 No. 215, Lianhe North Road, Fengxian District, Shanghai, China



WECHAT