

# EVALENE® LLDPE LJ20241

Linear Low Density Polyethylene

JG Summit Petrochemical Corporation

## Message:

LLDPE is used for heavy-duty sacks, lamination films, industrial cosmetics, pharmaceutical and food packaging materials.

Low Heat Seal Temperatures. Strong Seals. Excellent Tear, Puncture and Impact Strengths.

These properties make Evalene® the best choice for LLDPE packaging films. Its outstanding environmental stress crack resistance, good impact properties at low temperatures, and warp resistance also make it attractive for injection molding applications.

General Information			
Features	Good Processability		
	Good Tear Strength		
	High ESCR (Stress Crack Resist.)		
	High Gloss		
	High Impact Resistance		
	Low Temperature Heat Sealability		
	Low Temperature Impact Resistance		
	Puncture Resistant		
	Warp Resistant		
Uses	Color Concentrates		
	Lids		
	Toys		
Agency Ratings	FDA 21 CFR 177.1520		
Forms	Pellets		
Processing Method	Injection Molding		
Physical	Nominal Value	Unit	Test Method
Density	0.924	g/cm <sup>3</sup>	ASTM D1505
Melt Mass-Flow Rate (MFR) (190°C/2.16 kg)	20	g/10 min	ASTM D1238
Mechanical	Nominal Value	Unit	Test Method
Tensile Modulus <sup>1</sup>	250	MPa	ASTM D638
Tensile Strength <sup>2</sup> (Yield)	10.0	MPa	ASTM D638
Tensile Elongation <sup>3</sup> (Break)	> 1000	%	ASTM D638
NOTE			
1.	5.0 mm/min		
2.	50 mm/min		
3.	50 mm/min		

The information and data on this page are provided by manufacturers and document providers. SHANGHAI SUSHENG assumes no legal liability. It is strongly recommended to verify all technical data with material suppliers before final material selection. All rights belong to the original authors. If any infringement occurs, please contact us immediately.

Recommended distributors for this material

## Susheng Import & Export Trading Co.,Ltd.

Tel: +86 21 5895 8519

Phone: +86 13424755533

Email: sales@su-jiao.com

No. 215, Lianhe North Road, Fengxian District, Shanghai, China



WECHAT