

Silamid® EFXSV10

Polyamide 6
Roonamid a.s.

Message:

Polyamide 6, type reinforced with short glass fibres, high rigidity, shape stability, non halogenic flame retardant, natural, grey (RAL 7035) and black, optimal flow properties. Suitable for injection mouldings in electrotechnics.

General Information				
Filler / Reinforcement		Glass Fiber		
Features		Flame Retardant		
		Good Dimensional Stability		
		Good Flow		
		Halogen Free		
		High Rigidity		
Uses		Electrical/Electronic Applications		
Appearance		Black		
		Grey		
		Natural Color		
Forms		Pellets		
Processing Method		Injection Molding		
Physical	Dry	Conditioned	Unit	Test Method
Density	1.23	1.23	g/cm ³	ISO 1183
Melt Mass-Flow Rate (MFR) (230°C/2.16 kg)	6.0	6.0	g/10 min	ISO 1133
Molding Shrinkage				
Across Flow	1.5	1.5	%	
Flow	0.45	0.45	%	
Water Absorption (23°C, 24 hr)	1.0	1.0	%	ISO 62
Mechanical	Dry	Conditioned	Unit	Test Method
Tensile Modulus	5500	--	MPa	ISO 527-2
Tensile Stress (Break)	100	--	MPa	ISO 527-2
Impact	Dry	Conditioned	Unit	Test Method
Charpy Notched Impact Strength (23°C)	5.0	--	kJ/m ²	ISO 179/1eA
Charpy Unnotched Impact Strength (23°C)	35	--	kJ/m ²	ISO 179/1eU
Thermal	Dry	Conditioned	Unit	Test Method

Heat Deflection Temperature (1.8 MPa, Unannealed)	165	--	°C	ISO 75-2/A
Electrical	Dry	Conditioned	Unit	Test Method
Surface Resistivity	--	1.0E+12	ohms	IEC 60093
Volume Resistivity	--	1.0E+11	ohms·cm	IEC 60093
Electric Strength	--	15	kV/mm	IEC 60243-1
Relative Permittivity (1 MHz)	--	4.50		IEC 60250
Dissipation Factor (1 MHz)	--	0.10		IEC 60250
Arc Resistance	70.0	--	sec	ASTM D495
Comparative Tracking Index (Solution A)	--	400	V	IEC 60112
Flammability	Dry	Conditioned	Unit	Test Method
Flame Rating	V-2	--		UL 94
Glow Wire Ignition Temperature ¹	905	905	°C	IEC 60695-2-13
Injection	Dry	Unit		
Drying Temperature	< 80.0		°C	
Suggested Max Moisture	0.10		%	
Processing (Melt) Temp	250 to 280		°C	
Mold Temperature	60.0 to 80.0		°C	
NOTE				

1. Range: 850 to 960°C

The information and data on this page are provided by manufacturers and document providers. SHANGHAI SUSHENG assumes no legal liability. It is strongly recommended to verify all technical data with material suppliers before final material selection. All rights belong to the original authors. If any infringement occurs, please contact us immediately.

Recommended distributors for this material

Susheng Import & Export Trading Co.,Ltd.

Tel: +86 21 5895 8519

Phone: +86 13424755533

Email: sales@su-jiao.com

No. 215, Lianhe North Road, Fengxian District, Shanghai, China



WECHAT