

Geon™ Vinyl Flexible C7000

Flexible Polyvinyl Chloride

PolyOne Corporation

Message:

Geon™ Vinyl Flexible C7000 is a Flexible Polyvinyl Chloride product. It can be processed by coextrusion, extrusion, or injection molding and is available in Africa & Middle East, Asia Pacific, Europe, Latin America, or North America. Applications of Geon™ Vinyl Flexible C7000 include plumbing/piping/potable water and sealing applications. Primary characteristic: flame rated.

General Information	
UL YellowCard	E41877-234231
Features	General Purpose
	Medium Gloss
Uses	General Purpose
	Seals
	Weatherstripping
Agency Ratings	NSF 51 3
Forms	Pellets
Processing Method	Coextrusion
	Extrusion
	Injection Molding

Physical	Nominal Value	Unit	Test Method
Specific Gravity	1.39	g/cm ³	ASTM D792
Hardness	Nominal Value	Unit	Test Method
Durometer Hardness			ASTM D2240
Shore A	70		
Shore A, 15 sec	64		
Mechanical	Nominal Value	Unit	Test Method
Tensile Strength ¹			ASTM D638
Break	10.1	MPa	
100% Strain	4.34	MPa	
Tensile Elongation ² (Break)	390	%	ASTM D638
Elastomers	Nominal Value	Unit	Test Method
Tear Strength ³	35.0	kN/m	ASTM D624
Compression Set (23°C, 22 hr)	20	%	ASTM D395
Clash-Berg Modulus			ASTM D1043
--	81.4	MPa	
-46°C	310	MPa	
Thermal	Nominal Value	Unit	Test Method

Brittleness Temperature	-42.2	°C	ASTM D746
Flammability	Nominal Value		Test Method
Flame Rating	HB		UL 94
Injection	Nominal Value	Unit	
Processing (Melt) Temp	193 to 199	°C	
Extrusion	Nominal Value	Unit	
Melt Temperature	171 to 177	°C	
NOTE			
1.	510 mm/min		
2.	510 mm/min		
3.	Die C, 510 mm/min		

The information and data on this page are provided by manufacturers and document providers. SHANGHAI SUSHENG assumes no legal liability. It is strongly recommended to verify all technical data with material suppliers before final material selection. All rights belong to the original authors. If any infringement occurs, please contact us immediately.

Recommended distributors for this material

Susheng Import & Export Trading Co.,Ltd.

Tel: +86 21 5895 8519

Phone: +86 13424755533

Email: sales@su-jiao.com

No. 215, Lianhe North Road, Fengxian District, Shanghai, China

