Huafon JF-W-3130

Polyurethane

Huafon Group Co., Ltd.

Message:

General Type Characteristics Mid hard type, close and uniform cell structure, good film thickness, suit for glossy leather with small crease. Applications Shoes, Bags

14.0 to 16.0

> 35.0

General Information			
Features	Medium Hardness		
Uses	Bags		
	Footwear		
Additional Information	Nominal Value	Unit	
Solvents	DMF		
Uncured Properties	Nominal Value	Unit	
Solids Content	29 to 31	%	
Viscosity (25°C)	160 to 260	Pa·s	
Cured Properties	Nominal Value	Unit	

Tensile Elongation at Break > 250 % The information and data on this page are provided by manufacturers and document providers. SHANGHAI SUSHENG assumes no legal liability. It is strongly recommended to verify all technical data with material suppliers before final material selection.All rights belong to the original authors. If any

MPa

MPa

Recommended distributors for this material

infringement occurs, please contact us immediately.

Susheng Import & Export Trading Co.,Ltd.

Tel: +86 21 5895 8519

Phone: +86 13424755533

Tensile Modulus (100% Secant)

Tensile Strength

Email: sales@su-jiao.com

No. 215, Lianhe North Road, Fengxian District, Shanghai, China

