

Milastomer™ 8030NHS

Thermoplastic Vulcanizate

Mitsui Chemicals America, Inc.

Message:

Milastomer™8030NHS is a thermoplastic vulcanized rubber (TPV) material. This product is available in North America and is processed by extrusion or calendering.

General Information			
Appearance	Natural color		
Forms	Particle		
Processing Method	Extrusion		
	Calendering		
Physical	Nominal Value	Unit	Test Method
Density	0.880	g/cm ³	ASTM D1505
Melt Mass-Flow Rate (MFR) (230°C/10.0 kg)	9.3	g/10 min	ISO 1133
Hardness	Nominal Value	Unit	Test Method
Durometer Hardness			ISO 48
Shaw A	88		ISO 48
Shaw A, 5 seconds	84		ISO 48
Elastomers	Nominal Value	Unit	Test Method
Tensile Stress ¹ (100% Strain)	4.60	MPa	ISO 37
Tensile Stress ² (Break)	8.10	MPa	ISO 37
Tensile Elongation ³ (Break)	520	%	ISO 37
Thermal	Nominal Value	Unit	Test Method
Brittleness Temperature	< -60.0	°C	Internal method
Additional Information			
All tests performed according to Mitsui methods.			
NOTE			
1.	500 mm/min		
2.	500 mm/min		
3.	500 mm/min		

The information and data on this page are provided by manufacturers and document providers. SHANGHAI SUSHENG assumes no legal liability. It is strongly recommended to verify all technical data with material suppliers before final material selection. All rights belong to the original authors. If any infringement occurs, please contact us immediately.

Recommended distributors for this material

Susheng Import & Export Trading Co.,Ltd.

Tel: +86 21 5895 8519

Phone: +86 13424755533

Email: sales@su-jiao.com

No. 215, Lianhe North Road, Fengxian District, Shanghai, China

