Razalen® P121 GR30

Polypropylene Impact Copolymer Razin™ Engineering Plastics

Message:

Razalen P121 GR30 is an injection grade black color impact copolymer polypropylene reinforced with 30% glass fiber. It combines good toughness rigidity balance. Typical applications include automotive under hood application.

General Information			
Filler / Reinforcement	Glass Fiber,30% Filler by Weight		
Additive	Impact Modifier		
Features	Good Impact Resistance		
	Good Toughness		
	Impact Copolymer		
	Impact Modified		
	Medium Rigidity		
Uses	Automotive Applications		
	Automotive Under the Hood		
Appearance	Black		
Processing Method	Injection Molding		
Physical	Nominal Value	Unit	Test Method
Specific Gravity	1.14	g/cm³	ASTM D792
Melt Mass-Flow Rate (MFR) (230°C/2.16			
kg)	4.0	g/10 min	ASTM D1238
Molding Shrinkage - Flow	0.30	%	ASTM D955
Mechanical	Nominal Value	Unit	Test Method
Tensile Strength (Yield)	70.0	MPa	ASTM D638
Tensile Elongation (Break)	3.0	%	ASTM D638
Flexural Modulus	5100	MPa	ASTM D790
Flexural Strength	100	MPa	ASTM D790
Impact	Nominal Value	Unit	Test Method
Notched Izod Impact (Area) (23°C)	14.0	kJ/m²	ASTM D256
Thermal	Nominal Value	Unit	Test Method
Deflection Temperature Under Load			ASTM D648
0.45 MPa, Unannealed	155	°C	
1.8 MPa, Unannealed	140	°C	
Injection	Nominal Value	Unit	
Drying Temperature	80.0 to 100	°C	
Drying Time	2.0 to 4.0	hr	

Middle Temperature	210 to 220	°C
Front Temperature	220 to 230	°C
Processing (Melt) Temp	220 to 240	°C
Mold Temperature	40.0 to 80.0	°C
Injection Pressure	50.0 to 150	MPa

The information and data on this page are provided by manufacturers and document providers. SHANGHAI SUSHENG assumes no legal liability. It is strongly recommended to verify all technical data with material suppliers before final material selection. All rights belong to the original authors. If any infringement occurs, please contact us immediately.

Recommended distributors for this material

Susheng Import & Export Trading Co.,Ltd.

Tel: +86 21 5895 8519

Phone: +86 13424755533 Email: sales@su-jiao.com

No. 215, Lianhe North Road, Fengxian District, Shanghai, China

