

SMOKEGUARD™ III 1022 NATURAL

Polyvinyl Chloride

AlphaGary

Message:

A LEAD FREE, HIGHLY FLAME RETARDED, 75°C RATED, LOW SMOKE JACKETING COMPOUND FOR PLENUM CABLE CONSTRUCTIONS REQUIRING COMPLIANCE TO U.L. SUBJECT 910 MODIFIED STEINER TUNNEL. TEST

General Information			
Features	Low (to no) lead content		
	Low smoke		
	Flame retardancy		
Uses	Ceiling compartment cable sheath material		
Agency Ratings	UL not rated		
Appearance	Natural color		
Forms	Particle		
Processing Method	Extrusion		
Physical	Nominal Value	Unit	Test Method
Specific Gravity	1.60 - 1.64	g/cm ³	ASTM D792
Hardness	Nominal Value	Unit	Test Method
Durometer Hardness			ASTM D2240
Shaw D	67 - 73		ASTM D2240
Shaw D, 15 seconds	55 - 61		ASTM D2240
Elastomers	Nominal Value	Unit	Test Method
Tensile Strength			ASTM D412
0.381 mm	17.2	MPa	ASTM D412
1.91 mm	15.2	MPa	ASTM D412
Tensile Elongation			ASTM D412
Fracture, 1.91mm	200	%	ASTM D412
Fracture, 0.381mm	190	%	ASTM D412
Thermal	Nominal Value	Unit	Test Method
Brittleness Temperature	-6.00	°C	ASTM D746
Electrical	Nominal Value	Unit	Test Method
Dielectric Constant (23°C, 100 MHz)	3.60		ASTM D150
Dissipation Factor (23°C, 100 MHz)	0.019		ASTM D150
Flammability	Nominal Value	Unit	Test Method
Oxygen Index (3.18 mm)	54	%	ASTM D2863
Smoke	5.0	%	ASTM D4100
Extruder Screw Compression Ratio	3.0:1.0		
Extrusion	Nominal Value	Unit	

Cylinder Zone 1 Temp.	149	°C
Cylinder Zone 2 Temp.	154	°C
Cylinder Zone 3 Temp.	163	°C
Cylinder Zone 4 Temp.	168	°C
Cylinder Zone 5 Temp.	168	°C
Adapter Temperature	154	°C
Melt Temperature	179 - 185	°C
Die Temperature	154	°C

Extrusion instructions

Melt temperature is critical @ temperatures above 370 degrees F foaming may occur. It may be necessary to adjust barrel temp to attain the desired melt temperature. Material should be dried prior to use

The information and data on this page are provided by manufacturers and document providers. SHANGHAI SUSHENG assumes no legal liability. It is strongly recommended to verify all technical data with material suppliers before final material selection. All rights belong to the original authors. If any infringement occurs, please contact us immediately.

Recommended distributors for this material

Susheng Import & Export Trading Co.,Ltd.

Tel: +86 21 5895 8519

Phone: +86 13424755533

Email: sales@su-jiao.com

No. 215, Lianhe North Road, Fengxian District, Shanghai, China

