

Kuraray R-Polymer R-1130

Polyvinyl Alcohol

Kuraray Co., Ltd.

Message:

Modified

General Information			
Features	Biodegradable		
	Water Soluble		
Uses	Adhesives		
	Paper Coatings		
Forms	Granules		
Physical	Nominal Value	Unit	Test Method
Solution Viscosity ¹	20 to 30	mPa · s	DIN 53015
Ash Content ²	0.50	%	
Volatile Matter	5.0	%	
Degree of Hydrolysis	98 to 99	%	
NOTE			
1.	4 % aqueous solution at 20 °C determined by Brookfield synchronized-motor rotary-type visometer		
2.	Calculated as Na2O		

The information and data on this page are provided by manufacturers and document providers. SHANGHAI SUSHENG assumes no legal liability. It is strongly recommended to verify all technical data with material suppliers before final material selection. All rights belong to the original authors. If any infringement occurs, please contact us immediately.

Recommended distributors for this material

Susheng Import & Export Trading Co., Ltd.

Tel: +86 21 5895 8519

Phone: +86 13424755533

Email: sales@su-jiao.com

No. 215, Lianhe North Road, Fengxian District, Shanghai, China

