

# CALP FR913-1

Polyolefin

Lion Idemitsu Composites Co., Ltd.

Message:

CALP FR913-1 is a Polyolefin product. It can be processed by injection molding and is available in Asia Pacific.

Characteristics include:

- Flame Rated
- Flame Retardant
- Halogen Free

General Information			
Features	Bromine Free		
	Flame Retardant		
Processing Method	Injection Molding		
Physical	Nominal Value	Unit	Test Method
Specific Gravity	1.03	g/cm <sup>3</sup>	ASTM D792
Melt Mass-Flow Rate (MFR)	16	g/10 min	ASTM D1238
Molding Shrinkage			Internal Method
Flow : 2.00 mm	1.1	%	
Across Flow : 2.00 mm	1.3	%	
Hardness	Nominal Value	Unit	Test Method
Rockwell Hardness (R-Scale)	83		ASTM D785
Mechanical	Nominal Value	Unit	Test Method
Tensile Strength	21.0	MPa	ASTM D638
Tensile Elongation (Break)	24	%	ASTM D638
Flexural Modulus	1870	MPa	ASTM D790
Flexural Strength	35.0	MPa	ASTM D790
Impact	Nominal Value	Unit	Test Method
Notched Izod Impact (Area) (23°C)	4.10	kJ/m <sup>2</sup>	ASTM D256
Thermal	Nominal Value	Unit	Test Method
Deflection Temperature Under Load (0.45 MPa, Unannealed)	124	°C	ASTM D648
Ball Pressure Test (145°C)	Pass		Internal Method
RTI Elec	65.0	°C	UL 746
RTI Imp	65.0	°C	UL 746
RTI Str	65.0	°C	UL 746
Flammability	Nominal Value	Test Method	
Flame Rating (1.50 mm)	V-0	UL 94	

The information and data on this page are provided by manufacturers and document providers. SHANGHAI SUSHENG assumes no legal liability. It is strongly recommended to verify all technical data with material suppliers before final material selection.All rights belong to the original authors. If any infringement occurs, please contact us immediately.

Recommended distributors for this material

## Susheng Import & Export Trading Co.,Ltd.

Tel: +86 21 5895 8519

Phone: +86 13424755533

Email: sales@su-jiao.com

No. 215, Lianhe North Road, Fengxian District, Shanghai, China



WECHAT