

SABIC® LDPE HP2023N

Low Density Polyethylene

SABIC Americas, Inc.

Message:

PRODUCT DESCRIPTION:

SABIC® LDPE HP2023N is a Low Density Polyethylene grade without slip and anti-block additives. It typically exhibits better draw down ability with high output. Films typically exhibit good optics and good heat seal properties.

TYPICAL APPLICATIONS:

Bags & pouches, general purpose film.

This product is not intended for use in medical and pharmaceutical applications.

General Information			
Features	Low density		
	Optical		
	Good stripping		
	Good heat sealability		
	Compliance of Food Exposure		
Uses	Films		
	Bags		
Forms	Particle		
Processing Method	Blow film		
Physical	Nominal Value	Unit	Test Method
Density (23°C)	0.923	g/cm ³	ISO 1183
Melt Mass-Flow Rate (MFR) (190°C/2.16 kg)	2.0	g/10 min	ISO 1133
Mechanical	Nominal Value	Unit	Test Method
Tensile Modulus (0.0500 mm)	260	MPa	ISO 527-2
Tensile Stress (yield, 0.0500mm)	11.0	MPa	ISO 527-2
Coefficient of Friction	> 80	%	ISO 8295
Blow-up Ratio	2.00 - 3.00		
Films	Nominal Value	Unit	Test Method
Film Thickness - Tested	50	µm	
Film Thickness - Recommended / Available	20 - 100 micron		
Tensile Stress			ISO 527-3
MD: Broken, 50 µm, blown film	25.0	MPa	ISO 527-3
TD: Broken, 50 µm, blown film	21.0	MPa	ISO 527-3
Tensile Elongation			ISO 527-3
MD: Broken, 50 µm, blown film	250	%	ISO 527-3
TD: Broken, 50 µm, blown film	600	%	ISO 527-3
Dart Drop Impact (50 µm, Blown Film)	110	g	ASTM D1709

Thermal	Nominal Value	Unit	Test Method
Vicat Softening Temperature	94.0	°C	ISO 306/A50
Melting Temperature (DSC)	111	°C	ISO 3146
Optical	Nominal Value	Unit	Test Method
Gloss			ASTM D2457
20, 50.0 µm, blown film	> 50		ASTM D2457
60, 50.0 µm, blown film	> 100		ASTM D2457
Haze (50.0 µm, Blown Film)	< 8.0	%	ASTM D1003
Additional Information	Nominal Value		
Measured on 50 micron thickness blown film extruded at melt temperature of 180°C with BUR of 2.5			
Extrusion	Nominal Value	Unit	
Melt Temperature	160 - 200	°C	

The information and data on this page are provided by manufacturers and document providers. SHANGHAI SUSHENG assumes no legal liability. It is strongly recommended to verify all technical data with material suppliers before final material selection. All rights belong to the original authors. If any infringement occurs, please contact us immediately.

Recommended distributors for this material

Susheng Import & Export Trading Co.,Ltd.

Tel: +86 21 5895 8519

Phone: +86 13424755533

Email: sales@su-jiao.com

No. 215, Lianhe North Road, Fengxian District, Shanghai, China

