

COPEC® CC7OCZ (Series: VS/AD1)

Thermoplastic Elastomer

KRAIBURG TPE

Message:

The VS/AD1 Series is your material solution for applications in the consumer electronics section. The compounds feature an exceptionally silky and velvety surface, accompanied by excellent adhesion properties to polar thermoplastics such as ABS, PC and PC/ABS.

Typical applications

Ear phones

Game consoles

Handles and grips for consumer applications

Remote controls

Seals

Material advantages

Easy coloring (compounds in natural colors)

Excellent color stability

Good weathering resistance

Insert molding possible

Pleasant surface feel (Soft touch)

Resistance against skin oil, sunscreens and olive oil

Smooth and silky surface

UL 94 HB listed

General Information	
UL YellowCard	E214822-101550670
Features	Good Adhesion
	Good Color Stability
	Good Weather Resistance
	Oil Resistant
	Soft
Uses	Consumer Applications
	Electrical/Electronic Applications
	Handles
	Seals
Appearance	Black
Processing Method	Extrusion
	Injection Molding

Physical	Nominal Value	Unit	Test Method
Density	1.28	g/cm³	ISO 1183
Hardness	Nominal Value	Unit	Test Method
Shore Hardness (Shore A)	68		ISO 7619
Elastomers	Nominal Value	Unit	Test Method
Tensile Stress ¹ (Yield)	6.50	MPa	ISO 37

Tensile Elongation ² (Break)	900	%	ISO 37
Tear Strength ³	28	kN/m	ISO 34-1
Compression Set ⁴			ISO 815
23°C, 72 hr	16	%	
70°C, 24 hr	52	%	
100°C, 24 hr	70	%	
Flammability	Nominal Value		Test Method
Flame Rating	HB		UL 94
Additional Information	Nominal Value	Unit	Test Method
Adhesion to ABS	22.0	kN/m	Renault D41/1916
Adhesion to PC	30.0	kN/m	Renault D41/1916
Extrusion	Nominal Value		Unit
Drying Temperature	80.0	°C	
Drying Time	4.0	hr	
Suggested Max Moisture	0.020	%	
Cylinder Zone 1 Temp.	160	°C	
Cylinder Zone 2 Temp.	180	°C	
Cylinder Zone 3 Temp.	200	°C	
Die Temperature	220	°C	
NOTE			
1.	Type S2, 200 mm/min		
2.	Type S2, 200 mm/min		
3.	Method Bb, Angle (Nicked)		
4.	Method A		

The information and data on this page are provided by manufacturers and document providers. SHANGHAI SUSHENG assumes no legal liability. It is strongly recommended to verify all technical data with material suppliers before final material selection. All rights belong to the original authors. If any infringement occurs, please contact us immediately.

Recommended distributors for this material

Susheng Import & Export Trading Co.,Ltd.

Tel: +86 21 5895 8519

Phone: +86 13424755533

Email: sales@su-jiao.com

No. 215, Lianhe North Road, Fengxian District, Shanghai, China

