

PERCOM® DHG10

Polypropylene Homopolymer

A. Schulman Europe

Message:

PERCOM® DHG10 is a Polypropylene Homopolymer (PP Homopolymer) material filled with 10% glass fiber. It is available in Africa & Middle East, Asia Pacific, Europe, Latin America, or North America.

Important attributes of PERCOM® DHG10 are:

Flame Rated

RoHS Compliant

Homopolymer

Typical applications include:

Automotive

Tanks

General Information			
Filler / Reinforcement	Glass Fiber,10% Filler by Weight		
Features	Homopolymer		
Uses	Automotive Applications		
	Tanks		
RoHS Compliance	RoHS Compliant		
Physical	Nominal Value	Unit	Test Method
Density	0.970	g/cm ³	ISO 1183
Melt Mass-Flow Rate (MFR) (230°C/2.16 kg)	2.5	g/10 min	ISO 1133
Molding Shrinkage	0.80 to 1.5	%	
Hardness	Nominal Value	Unit	Test Method
Shore Hardness (Shore D)	63		
Mechanical	Nominal Value	Unit	Test Method
Tensile Stress (Break)	65.0	MPa	ISO 527-2
Flexural Modulus	2700	MPa	ISO 178
Impact	Nominal Value	Unit	Test Method
Notched Izod Impact Strength (23°C)	11	kJ/m ²	ISO 180/1A
Thermal	Nominal Value	Unit	Test Method
Heat Deflection Temperature			
0.45 MPa, Unannealed	140	°C	ISO 75-2/B
1.8 MPa, Unannealed	115	°C	ISO 75-2/A
Vicat Softening Temperature	150	°C	ISO 306/A50
Flammability	Nominal Value	Test Method	
Flame Rating	HB	UL 94	

The information and data on this page are provided by manufacturers and document providers. SHANGHAI SUSHENG assumes no legal liability. It is strongly recommended to verify all technical data with material suppliers before final material selection.All rights belong to the original authors. If any infringement occurs, please contact us immediately.

Recommended distributors for this material

Susheng Import & Export Trading Co.,Ltd.

Tel: +86 21 5895 8519

Phone: +86 13424755533

Email: sales@su-jiao.com

No. 215, Lianhe North Road, Fengxian District, Shanghai, China



WECHAT