

# DynaPath™ XP-3065 TC

Polysulfone

Polymer Dynamix

## Message:

Thermally Conductive Specialty Polysulfone

Features:

Thermally Conductive

General Information		
Processing Method	Extrusion	
Extrusion	Nominal Value	Unit
Drying Temperature	132 - 149	°C
Drying Time	3.0 - 5.0	hr
Cylinder Zone 1 Temp.	171 - 182	°C
Cylinder Zone 3 Temp.	177 - 188	°C
Cylinder Zone 5 Temp.	182 - 193	°C
Melt Temperature	191 - 199	°C
Die Temperature	191 - 199	°C

## Extrusion instructions

Extrusion - A barrier screw with a mixing section having a compression ratio of at least 2.5:1 is recommended. During continuous processing, it is recommended to keep the melt temperature below 400°C for better physical properties and aesthetics.

The information and data on this page are provided by manufacturers and document providers. SHANGHAI SUSHENG assumes no legal liability. It is strongly recommended to verify all technical data with material suppliers before final material selection. All rights belong to the original authors. If any infringement occurs, please contact us immediately.

## Recommended distributors for this material

### Susheng Import & Export Trading Co.,Ltd.

Tel: +86 21 5895 8519

Phone: +86 13424755533

Email: sales@su-jiao.com

No. 215, Lianhe North Road, Fengxian District, Shanghai, China

