

Latene® AG7H G/30

Polypropylene Homopolymer

LATI S.p.A.

Message:

Polypropylene homopolymer (PPh) based compound.

Fibres chemically coupled. Heat stabilised. Glass fibres. Good thermal properties.

General Information			
Filler / Reinforcement	Glass Fiber,30% Filler by Weight		
Additive	Heat Stabilizer		
Features	Chemically Coupled		
	Heat Stabilized		
	Homopolymer		

Physical	Nominal Value	Unit	Test Method
Density	1.12	g/cm ³	ISO 1183
Molding Shrinkage ¹			ISO 294-4
Across Flow : 2.00 mm	0.40 to 0.80	%	
Flow : 2.00 mm	0.030 to 0.70	%	
Water Absorption (23°C, 24 hr)	0.050	%	ISO 62

Mechanical	Nominal Value	Unit	Test Method
Tensile Modulus			ISO 527-2/1
23°C	6300	MPa	
60°C	4500	MPa	
90°C	3300	MPa	
Tensile Stress			ISO 527-2/5
Break, 23°C	80.0	MPa	
Break, 60°C	55.0	MPa	
Break, 90°C	40.0	MPa	
Tensile Strain			ISO 527-2/5
Break, 23°C	3.0	%	
Break, 60°C	3.5	%	
Break, 90°C	6.0	%	

Impact	Nominal Value	Unit	Test Method
Charpy Notched Impact Strength (23°C)	10	kJ/m ²	ISO 179/1eA
Charpy Unnotched Impact Strength (23°C)	65	kJ/m ²	ISO 179/1eU

Thermal	Nominal Value	Unit	Test Method
Heat Deflection Temperature			
0.45 MPa, Unannealed	155	°C	ISO 75-2/B
1.8 MPa, Unannealed	135	°C	ISO 75-2/A

Continuous Use Temperature ²	120	°C	
Vicat Softening Temperature	135	°C	ISO 306/B50
CLTE - Flow (30 to 100°C)	2.0E-5	cm/cm/°C	ISO 11359-2
Flammability	Nominal Value		Test Method
Flame Rating (1.50 mm)	HB		UL 94
Injection	Nominal Value	Unit	
Drying Temperature	80.0 to 90.0	°C	
Drying Time	3.0	hr	
Suggested Max Regrind	15	%	
Processing (Melt) Temp	200 to 240	°C	
Mold Temperature	40.0 to 60.0	°C	
Injection Rate	Moderate		
NOTE			
1.	60 MPa		
2.	20,000 hr		

The information and data on this page are provided by manufacturers and document providers. SHANGHAI SUSHENG assumes no legal liability. It is strongly recommended to verify all technical data with material suppliers before final material selection. All rights belong to the original authors. If any infringement occurs, please contact us immediately.

Recommended distributors for this material

Susheng Import & Export Trading Co.,Ltd.

Tel: +86 21 5895 8519

Phone: +86 13424755533

Email: sales@su-jiao.com

No. 215, Lianhe North Road, Fengxian District, Shanghai, China

