Vydyne® 88X

Polyamide 66/6 Copolymer

Ascend Performance Materials Operations LLC

Message:

Vydyne 88X is a medium-viscosity PA66/6 random copolymer used for extrusion-compounding. It provides benefits for compounds containing heat-sensitive additives and for end applications that require good surface finish. This copolymer is specifically designed to be used with FR packages and high mineral loadings. Vydyne 88X is the product of choice for low-yellowness-required applications. Vydyne 88X maintains the chemical resistance typical of PA66/6 to many chemicals, machine and motor oils, solvents and gasoline.

Typical Applications/End Uses:

Compounding

General Information			
Features	Copolymer		
	Gasoline Resistance		
	General Purpose		
	Good Abrasion Resistance		
	Good Chemical Resistance		
	Good Toughness		
	High Rigidity		
	High Strength		
	Oil Resistant		
	Solvent Resistant		
Uses	Compounding		
	General Purpose		
Agency Ratings	EC 1935/2004		
	EU 10/2011		
	EU 2023/2006		
	FDA 21 CFR 177.1500		
Appearance	Natural Color		
Forms	Pellets		
Processing Method	Compounding		
	Compounding Extrusion		
Physical	Nominal Value	Unit	Test Method
Density	1.14	g/cm³	ISO 1183
Viscosity Number (H2SO4 (Sulphuric Acid))	137 to 148	cm³/g	ISO 307
Bulk Density	674	g/l	ASTM D1895
Moisture Content	0.50	%	ASTM D6869
Relative Viscosity ¹	45.0 to 51.0		ASTM D789

Thermal	Nominal Value	Unit	Test Method
Melting Temperature	255	°C	ISO 11357-3
Optical	Nominal Value	Unit	Test Method
Yellowness Index	-4.0	YI	ASTM D1925
NOTE			
1.	Formic acid		

The information and data on this page are provided by manufacturers and document providers. SHANGHAI SUSHENG assumes no legal liability. It is strongly recommended to verify all technical data with material suppliers before final material selection. All rights belong to the original authors. If any infringement occurs, please contact us immediately.

Recommended distributors for this material

Susheng Import & Export Trading Co.,Ltd.

Tel: +86 21 5895 8519

Phone: +86 13424755533

Email: sales@su-jiao.com

No. 215, Lianhe North Road, Fengxian District, Shanghai, China

