## Loyblend® YA-1011FR

Acrylonitrile Butadiene Styrene + PBT

Colour Image Plastic Compound Sdn. Bhd. (CIPC)

## Message:

Loyblend® YA-1011FR is15% glass fiber flame retardant PBT/ABS polymer alloy compound. This grade offers excellent flame retardancy with balanced mechanical properties for applications such as portable appliance, facsimile machine, electrical components, etc.

General Information				
Filler / Reinforcement	Glass Fiber,15% Filler by Weight			
Additive	Flame Retardant			
Features	Flame Retardant			
	Low Density			
	Low Warpage			
Uses	Appliances			
	Business Equipment			
	Electrical Parts			
	Electrical/Electronic Applications			
Forms	Pellets			
Processing Method	Injection Molding			
Physical	Nominal Value	Unit	Test Method	
Specific Gravity	1.44	g/cm³	ASTM D792	
Molding Shrinkage - Flow (3.20 mm)	0.40 to 0.60	%	ASTM D955	
Water Absorption (24 hr)	0.15	%	ASTM D570	
Mechanical	Nominal Value	Unit	Test Method	
Tensile Modulus	5520	MPa	ASTM D638	
Tensile Strength	90.0	MPa	ASTM D638	
Tensile Elongation (Break)	2.5	%	ASTM D638	
Flexural Modulus	6000	MPa	ASTM D790	
Flexural Strength	136	MPa	ASTM D790	
Impact	Nominal Value	Unit	Test Method	
Notched Izod Impact (23°C)	82	J/m	ASTM D256	
Thermal	Nominal Value	Unit	Test Method	
Deflection Temperature Under Load (1.8 MPa, Unannealed, 4.00 mm)	76.0	°C	ASTM D648	
Flammability	Nominal Value		Test Method	
Flame Rating (1.60 mm)	V-0		UL 94	
Injection	Nominal Value	Unit		
Drying Temperature	80.0 to 90.0	°C		
Drying Time	4.0 to 6.0	hr		

Rear Temperature	230 to 240	°C	
Middle Temperature	235 to 245	°C	
Front Temperature	240 to 250	°C	
Nozzle Temperature	250 to 260	°C	
Mold Temperature	50.0 to 90.0	°C	

The information and data on this page are provided by manufacturers and document providers. SHANGHAI SUSHENG assumes no legal liability. It is strongly recommended to verify all technical data with material suppliers before final material selection. All rights belong to the original authors. If any infringement occurs, please contact us immediately.

## Recommended distributors for this material

## Susheng Import & Export Trading Co.,Ltd.

Tel: +86 21 5895 8519

Phone: +86 13424755533 Email: sales@su-jiao.com

No. 215, Lianhe North Road, Fengxian District, Shanghai, China

