

Unichem 8705FR-1

Polyvinyl Chloride

Colorite Polymers

Message:

Designed for 105 C operation.

General Information			
Additive	Flame Retardant		
Features	Flame Retardant		
	Good Flexibility		
Forms	Pellets		
Processing Method	Extrusion		
Physical	Nominal Value	Unit	Test Method
Specific Gravity	1.37	g/cm ³	ASTM D792
Hardness	Nominal Value	Unit	Test Method
Durometer Hardness (Shore A)	86		ASTM D2240
Mechanical	Nominal Value	Unit	Test Method
Tensile Strength (Yield)	17.2	MPa	ASTM D638
Tensile Elongation (Yield)	350	%	ASTM D638
Elastomers	Nominal Value	Unit	Test Method
Tensile Stress (100% Strain)	11.0	MPa	ASTM D412

The information and data on this page are provided by manufacturers and document providers. SHANGHAI SUSHENG assumes no legal liability. It is strongly recommended to verify all technical data with material suppliers before final material selection.All rights belong to the original authors. If any infringement occurs, please contact us immediately.

Recommended distributors for this material


Susheng Import & Export Trading Co.,Ltd.

Tel: +86 21 5895 8519

Phone: +86 13424755533

Email: sales@su-jiao.com

No. 215, Lianhe North Road, Fengxian District, Shanghai, China



WECHAT